**This is an electronic reprint of the original article.
This reprint *may differ* from the original in pagination and typographic detail.**

Author(s): Ghosh, Biswa Nath; Bhowmik, Sandip; Mal, Prasenjit; Rissanen, Kari

Title: A highly selective, Hg²⁺ triggered hydrogelation: modulation of morphology by chemical stimuli

Year: 2014

Version:

Please cite the original version:

Ghosh, B. N., Bhowmik, S., Mal, P., & Rissanen, K. (2014). A highly selective, Hg²⁺ triggered hydrogelation: modulation of morphology by chemical stimuli. *Chemical Communications*, 50(6), 734-736. <https://doi.org/10.1039/C3CC47591C>

All material supplied via JYX is protected by copyright and other intellectual property rights, and duplication or sale of all or part of any of the repository collections is not permitted, except that material may be duplicated by you for your research use or educational purposes in electronic or print form. You must obtain permission for any other use. Electronic or print copies may not be offered, whether for sale or otherwise to anyone who is not an authorised user.

ChemComm

Accepted Manuscript

This is an *Accepted Manuscript*, which has been through the RSC Publishing peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, which is prior to technical editing, formatting and proof reading. This free service from RSC Publishing allows authors to make their results available to the community, in citable form, before publication of the edited article. This *Accepted Manuscript* will be replaced by the edited and formatted *Advance Article* as soon as this is available.

To cite this manuscript please use its permanent Digital Object Identifier (DOI®), which is identical for all formats of publication.

More information about *Accepted Manuscripts* can be found in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics contained in the manuscript submitted by the author(s) which may alter content, and that the standard [Terms & Conditions](#) and the [ethical guidelines](#) that apply to the journal are still applicable. In no event shall the RSC be held responsible for any errors or omissions in these *Accepted Manuscript* manuscripts or any consequences arising from the use of any information contained in them.

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

COMMUNICATION

A Highly Selective, Hg^{2+} Triggered Hydrogelation: Modulation of Morphology by Chemical StimuliBiswa Nath Ghosh,^{‡a} Sandip Bhowmik,^{‡a} Prasenjit Mal^{*b} and Kari Rissanen^{*a}

Received (in XXX, XXX) Xth XXXXXXXXX 20XX, Accepted Xth XXXXXXXXX 20XX

DOI: 10.1039/b000000x

We report the first Hg^{2+} selective hydrogelation by 4'-[4-(4-aminophenyl)phenyl]-2,2':6',2''-terpyridine. The gel showed remarkable response towards specific chemical agents such as benzo-18-crown-6 ether and K^+ which enabled extensive modulation of the gel morphology.

In the past few decades, self-assembly of small molecules has been extensively used as an efficient strategy to build and modulate nanostructures. Low molecular weight supramolecular hydrogels have in particular found myriad applications in fields such as organic-inorganic hybrid materials,^{1,2} medicines,³ optoelectronics.⁴ One of the most important and desirable feature of these gels is the dynamic nature of the assemblies which allows structural modulations at the molecular level. Numerous such functional materials have been reported in recent literature where it was possible to modify the physical properties by applying external stimuli such as pH,⁵ photons,⁶ chemical agents.^{7,8} This has also encouraged the use of such responsive supramolecular assemblies as potential indicator systems for changes in the immediate environment.⁹

Among various stimuli applied to modify gel behavior, metal ions have been one of the most common regulators. On several occasions, introduction of metal ion in the gelator media was shown to have triggered long range self-assemblies which ultimately resulted in the formation of 3D-gel network.¹⁰ In some cases, gelators had also been covalently modified with specific metal-binding motifs to impart selectivity.^{11,12}

Terpyridines are one of the most extensively used ligands to complex transition metal ions and had often served as a building block for supramolecular gel systems.¹³⁻¹⁵ The easy tunability of its physical properties by varying the metal ions made it a very promising prospect for such assemblies. However, due to their universal coordination ability the terpyridines lack the binding specificity towards any particular metal ion leading to a situation that the gelation process is not metal ion specific. Herein, we report formation of a supramolecular hydrogel of 4'-[4-(4-aminophenyl)phenyl]-2,2':6',2''-terpyridine **L** in presence of Hg^{2+} ion. The gel was formed under slightly acidic conditions and showed a remarkable selectivity towards Hg^{2+} in terms of the gelation behavior. To the best of our knowledge, this is the first report of a hydrogelation triggered specifically by divalent

mercury ion. In the course of detailed investigations we observed that significant control over the gel morphology could be achieved by addition of specific reagents, namely benzo-18-crown-6 (**B18-C-6**) and K^+ ions. Ligand **L** was synthesized by the Suzuki cross-coupling reaction between 4'-[4-(4-bromophenyl)-2,2':6',2''-terpyridine **1**¹⁶ and 4-aminophenylboronic acid pinacol ester **2** in dimethoxyethane solvent in the presence of Na_2CO_3 using $\text{Pd}(\text{PPh}_3)_4$ as catalyst (Scheme 1).

Scheme 1 Synthesis of **L**.

Ligand **L** was solubilized in aqueous solution of 0.2 N HCl. At this pH, the interactions (hydrogen bonding and electrostatics) between the partially protonated ligand (**L**) units were not able to form any kind of self-organized structures in aqueous media. However, the coordination of ligand **L** to metal ions was perceived to cause significant charge polarization in complexes, leading to stronger intermolecular interactions and self-assembly. Based on this, several metal ions were tested and disappointingly most of the earth alkaline and transition metal complexes (Fig. 1) precipitated out from the solution. However, $\text{Hg}(\text{II})$ showed remarkable ability to form hydrogels when added to aqueous solution of **L** (Fig. 1). Given the lack of any specific $\text{Hg}(\text{II})$ binding motif on ligand **L**, the high degree of selectivity of the gelation process towards $\text{Hg}(\text{II})$ was indeed intriguing.

Different ligand to Hg^{2+} ratios were studied in order to optimize the gelation process and hydrogelation occurred at Hg^{2+} :**L** ratio of 1:1. However, a visibly stronger gel was obtained when Hg^{2+} to ligand ratio was increased to 2:1 and thus this ratio was used for further studies. The formation of the gel was found to be hampered in the presence of other divalent metal ions in combination with Hg^{2+} (see ESI[†]). Though the reasons for this unusual selectivity are not perfectly understood, it can be assumed that the large size of the divalent mercury cation plays

Fig. 1 From left to right 12 mM of (chloride salt of) Mg^{2+} , Ca^{2+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Ni^{2+} , Cu^{2+} , Zn^{2+} , Cd^{2+} , Hg^{2+} in 6 mM of **L**.

an important role. As reported by Griffith *et al.* hexa-coordinated transition metal complexes of analogues terpyridines are not suitable for extended networks/structures due to geometrical constraints.¹⁴ However, HgCl_2 form penta-coordinated N_3Cl_2 terpyridine complexes owing to its larger size and can facilitate stronger $\pi\cdots\pi$ stacking interactions. The gel formed solely in presence of Hg^{2+} (and chloride anions) was thermo-irreversible and found to be thixotropic in nature. To better understand the morphological properties of the gel, morphology of the xerogel was elucidated by SEM (scanning electron microscopy) and TEM (transmission electron microscopy) techniques which revealed the structure of the gel matrix to consist of a uniform, dense network of very thin fibers (Fig. 2). The width of the fibers was determined by HRTEM to be ~ 10 nm.

Fig. 2 a) TEM (inset: HRTEM of single fiber, scale bar 100 nm) and b) SEM image of hydrogel of 12 mM Hg^{2+} in 6 mM of **L**.

In order to explain the aggregation behavior, crystal structure of the HgCl_2L complex was analyzed. Since it was extremely difficult to obtain single crystals under the exact conditions that led to gelation, the hydrogel was dissolved in DMF and slowly evaporated to yield yellow plate like single crystals of HgCl_2L . The mercury has distorted trigonal bipyramidal N_3Cl_2 coordination (Fig. 3a). Apart from the exception of the benzene ring between the terpyridine domain and aniline moiety, ligand **L** was otherwise observed to be planar. Analysis of the crystal packing revealed the presence of strong $\pi\cdots\pi$ interactions (3.26 Å) between the central pyridine ring of the terpyridine domain and the anilinic benzene ring of the adjacent complex. Additionally, moderate $\text{N-H}\cdots\text{Cl}$ interactions ($\text{H}\cdots\text{Cl} = 2.65$ Å) (between the terminal Cl atom and adjacent anilinic H-atoms) were also found to be present in a dimeric motif (Fig. 3b).

From the crystal packing of the HgCl_2L complex it can be concluded that in the gel the partially protonated aromatic amines (gel forms under mildly acidic conditions) play a key role in the self-assembly process. A control gelation experiment was also

carried out with 4'-[4-(4-phenyl)phenyl]-2,2':6',2''-terpyridine **L1** (without the amine functionality). However, addition of $\text{Hg}(\text{II})$ to its 0.2 N HCl solution results immediate precipitation of the metal complex (see ESI[†]).

Fig. 3 (a) ORTEP plot of the molecular structure of HgCl_2L . Thermal ellipsoids are shown at 30% probability level. Selected bond distances (Å) and angles (°): $\text{Hg}(1)\text{-N}(1)$ 2.395(7), $\text{Hg}(1)\text{-N}(2)$ 2.373(5), $\text{Hg}(1)\text{-N}(3)$ 2.437(7), $\text{Hg}(1)\text{-Cl}(1)$ 2.436(3), $\text{Hg}(1)\text{-Cl}(2)$ 2.461(2), $\text{Cl}(1)\text{-Hg}(1)\text{-Cl}(2)$ 106.52(10), $\text{N}(2)\text{-Hg}(1)\text{-N}(1)$ 68.6(2), $\text{N}(2)\text{-Hg}(1)\text{-N}(3)$ 67.8(2); (b) The dimeric motif in the crystal packing of HgCl_2L .

It was evident that manipulating the key interactions could in principle provide a certain degree of geometrical control over the aggregates which would indeed be advantageous in the formation of advanced soft materials. Actually Zhang *et al.*, have recently demonstrated the use of different metal complexes to predetermine the dimensionality of intermolecular interactions, enabling the construction of nanofibers with single-molecule width (3.1 ± 0.1 nm).¹⁷

In this context, we investigated how a crown ether, here **B18-C-6** would modify the aggregation behavior of **L** in presence of Hg^{2+} . Based on the ability of the crown ether to bind to the ammonium end of the complex and thus blocking of the growth of the fibrous assembly was envisaged. As expected the gel network collapsed after the addition of about 0.4 equivalents of **B18-C-6**. However, in the presence of 4.0 equivalents of K^+ along with **B18-C-6** in the acidic solution of **L**, addition of Hg^{2+} resulted in a visibly weaker gel (Fig.4), presumably due to the stronger binding of K^+ to the crown ether.

Fig. 4 12 mM of Hg^{2+} in 6 mM of **L** in 1) excess KCl and 2.5 mM **B18-C-6**; 2) in absence of any additives; 3) 2.5 mM **B18-C-6**.

Since the gel properties predominantly depend on its morphology, it was interesting to probe the changes in the Hg^{2+}L xerogel structure with TEM. The TEM images show that while the nanofibrillar network was completely destroyed upon the addition of **B18-C-6**, it was partially restored in the presence of K^+ . However, when compared to the original gel, the nanofibers formed in the presence of crown-ether and K^+ were found to be much shorter in length but at the same time appeared to be much thicker (20-30 nm).

Fig. 5 TEM and SEM micrograph of a) & b) Hydrogel of 12 mM of Hg^{2+} in 6 mM of **L**; c) & d) hydrogel in presence of 2.5 mM **B18-C-6** and e) & f) hydrogel in presence of excess KCl and 2.5 mM **B18-C-6**.

The shorter and thicker fibers formed a loosely packed network which led to a visibly weaker gel. Further evidence for the gel morphology was obtained through the scanning electron microscopy (SEM) analysis (Fig 5). Both TEM and SEM analysis confirmed the observed changes in the morphologies of the hydrogels under specific chemical stimuli. This clearly proves the significantly altered interactions at the molecular level and allows control over the gel morphology in the nanoscale domain, a much desired property in novel material design.

In conclusion, 4'-[4-(4-aminophenyl)phenyl]-2,2':6',2''-terpyridine was shown to form a thermo-irreversible, translucent, thixotropic, supramolecular hydrogel exclusively in the presence of Hg^{2+} under acidic conditions. The N_3Cl_2 coordination in the HgCl_2L complex was found to be imperative for gelation, an unusual and unprecedented example of Hg^{2+} selectivity. Other studied divalent transition metal cations did not form a gel on their own and further disrupted the gelation process when added in conjunction with Hg^{2+} . Strong $\pi\cdots\pi$ interactions between the terpyridine units coupled with the salt-bridge interactions

triggered by Hg^{2+} are likely to be the major driving force for the self-assembly process. The microscopy investigations revealed the gel structure to consist of thin fibrous (~10 nm) network. In addition the gel morphology was found to be chemo-responsive and could be extensively modulated by **B18-C-6** and K^+ ions. The responsive nature of the gel also provided valuable insights into the key molecular interactions which might be helpful in rationalizing the course of aggregation. These gels are currently being further investigated to explain the role of the mercury(II) cation in the gelation process and to elucidate the exact mode of self-assembly.

Mr. Petri Papponen and Mr. Hannu Salo are kindly acknowledged for their help in TEM and SEM measurements, respectively. Academy of Finland (KR. grant no. 256259, 265328 and 263256) and DST, India (PM, grant INT/FINLAND/P-06 and SR/S1/IC-59/2010) are kindly acknowledged for financial support.

Notes and references

^aDepartment of Chemistry, Nanoscience Center, University of Jyväskylä, P.O. Box 35, 40014 Jyväskylä, Finland.. Fax: +358 14 2602501; Tel: 358-50-5623721; E-mail: kari.t.rissanen@jyu.fi

^bSchool of Chemical Sciences, NISER, Bhubaneswar, Institute of Physics Campus, P.O. Sainik School, Bhubaneswar, Odisha 751005, India.

† These authors contributed equally to this work.

† Electronic Supplementary Information (ESI) available: [Experimental details, gelation procedure, X-ray single crystal structure analysis (CCDC 960506)]. See DOI: 10.1039/b000000x/.

- G. Raj, C. Swalus, A. Guillet, M. Devillers, B. Nysten and E. M. Gagneaux, *Langmuir*, 2013, **29**, 4388-4395.
- S. Banerjee, R. K. Das and U. Maitra, *J. Mater. Chem.*, 2009, **19**, 6649-6687.
- E. Busseron, Y. Ruff, E. Moulin and N. Giuseppone, *Nanoscale*, 2013, **5**, 7098-7140.
- S. Nardecchia, D. Carriazo, M. L. Ferrer, M. C. Gutiérrez and F. del Monte, *Chem. Soc. Rev.*, 2013, **42**, 794-830.
- J. H. Jung, H. Kobayashi, M. Masuda, T. Shimizu and S. Shinkai, *J. Am. Chem. Soc.*, 2001, **123**, 8785-8789.
- S. Kume, K. Kuroiwa and N. Kimizuka, *Chem. Commun.*, 2006, 2442-2444.
- C. M. Micklitsch, P. J. Knerr, M. C. Branco, R. Nagarkar, D. J. Pochan and J. P. Schneider, *Angew. Chem. Int. Ed.*, 2011, **50**, 1577-1579.
- T. H. Kim, M. S. Choi, B.-H. Sohn, S.-Y. Park, W. S. Lyoo and T. S. Lee, *Chem. Commun.*, 2008, 2364-2366.
- P. Anzenbacher Jr, P. Lubal, P. Buček, M. A. Palacios and M. E. Kozelkova, *Chem. Soc. Rev.*, 2010, **39**, 3954-3979.
- M.-O. M. Piepenbrock, G. O. Lloyd, N. Clarke and J. W. Steed, *Chem. Rev.*, 2010, **110**, 1960-2004.
- Q. Liu, Y. Wang, W. Li and L. Wu, *Langmuir*, 2007, **23**, 8217-8223.
- M. O. M. Piepenbrock, N. Clarke and J. W. Steed, *Soft Matter*, 2010, **6**, 3541-3547.
- W. Weng, J. B. Beck, A. M. Jamieson and S. J. Rowan, *J. Am. Chem. Soc.*, 2006, **128**, 11663-11672.
- A. Griffith, T. J. Bandy, M. Light and E. Stulz, *Chem. Commun.*, 2013, **49**, 731-733.
- F. D. Jochum, J. Brassine, C. A. Fustin and J. F. Gohy, *Soft Matter*, 2013, **9**, 2314-2320.
- F. S. Han, M. Higuchi and D. G. Kurth, *Org. Lett.*, 2007, **9**, 559-562.
- Y. Zhang, B. Zhang, Y. Kuang, Y. Gao, J. Shi, X. X. Zhang and B. Xu, *J. Am. Chem. Soc.*, 2013, **135**, 5008-5011.