

This is a self-archived version of an original article. This version may differ from the original in pagination and typographic details.

Author(s): Ghalibaf, Maryam; Ullah, Saleem; Alén, Raimo

Title: Fast pyrolysis of hot-water-extracted and soda-AQ-delignified okra (Abelmoschus esculentus) and miscanthus (miscanthus x giganteus) stalks by Py-GC/MS

Year: 2018

Version: Accepted version (Final draft)

Copyright: © 2018 Elsevier Ltd.

Rights: CC BY-NC-ND 4.0

Rights url: https://creativecommons.org/licenses/by-nc-nd/4.0/

Please cite the original version:

Ghalibaf, M., Ullah, S., & Alén, R. (2018). Fast pyrolysis of hot-water-extracted and soda-AQdelignified okra (Abelmoschus esculentus) and miscanthus (miscanthus x giganteus) stalks by Py-GC/MS. Biomass and Bioenergy, 118, 172-179. https://doi.org/10.1016/j.biombioe.2018.09.001

1	
2	
3	Pyrolytic behavior of lignocellulosics-based polysaccharides
4	
5	Maryam Ghalibaf ¹ *, Tharaka Rama Krishna C. Doddapaneni ² , Raimo Alén ¹
6	
7	¹ Laboratory of Applied Chemistry, University of Jyväskylä, P.O. Box 35, FI-40014 Jyväskylä, Finland
8	² Laboratory of Chemistry and Bioengineering, Tampere University of Technology, P.O. Box 541, FI- 33101
9	Tampere, Finland
10	
11	* Corresponding author.
12	E-mail address: maryam.m.ghalibaf@jyu.fi (M. Ghalibaf).
13	
14	Abstract
15	The thermochemical behavior of cellulose, glucomannan, and xylan was investigated by pyrolysis-gas
16	chromatography-mass spectrometry (Py-GC/MS). In each case, major GC-amenable condensable products were
17	classified into several compound groups, and the formation of these monomer-related fragments from the model
18	substance samples was determined at 500, 600, and 700 °C with a residence time of 5 s and 20 s. The results
19	revealed that despite some general formation trends, no compound group was selectively formed at certain
20	temperatures. Of the 11 product groups, the primary ones, including lactone, furan, and cyclopentenone derivatives,
21	accounted for 72-85% (from cellulose), 86-90% (from glucomannan), and 76-81% (from xylan) of the total amount
22	of pyrolysis products determined. At 500 °C, about half of the major product groups accounted for lactones, such as
23	3-hydroxy-2-penteno-1,5-lactone and 5H-furan-2-one. It was also confirmed by thermogravimetric analyses that
24	within the temperature range studied, cellulose was thermally more stable than the heterogeneous hemicelluloses.
25	These kinds of data are of importance, for example, with respect to efforts to develop new biorefinery possibilities
26	for renewable resources.
~-	

28 Keywords: Cellulose, Glucomannan, Xylan, Pyrolysis-gas chromatography, Condensable products,

29 Thermogravimetry

30

31 1. Introduction

32 The biorefinery concept can be defined merely as a process for fractionating and/or converting into energy 33 carbon dioxide-neutral feedstock (biomass) as well as a great variety of chemicals and other biomaterials in an 34 ecosystem-friendly way through advanced technologies [1,2]. The pulp industry, as an essential branch of global 35 industry, is based on vast and multidisciplinary technology. For example, a modern chemical pulp mill that employs 36 one fibrous feedstock is capable of manufacturing, besides pulp, several pulping by-products, and it can be 37 considered a rather sophisticated biorefinery. It is also known that the integration of a hot-water-extraction pre-38 treatment stage prior to alkaline pulping may offer a feasible possibility, mainly to recover the dissolved 39 carbohydrates-derived material for further utilization by biochemical and chemical technologies [3]. This concept of 40 an integrated forest biorefinery has been investigated under a variety of conditions and from several points of view. 41 In our earlier papers, we used pyrolysis-gas chromatography/mass spectrometry (Py-GC/MS) for revealing the 42 thermochemical behavior of silver birch [4] and Norway spruce [5] sawdust, as well as non-wood materials, such as 43 okra and miscanthus [6]. In all cases, the effects of pyrolysis conditions on the product distribution were studied. All 44 the materials were investigated as such and after hot-water extraction together with the pulps obtained from these 45 feedstocks by sulfur-free delignification. In each case, major GC-amenable condensable products were determined 46 and classified into several compound groups, characteristically originated from the main structural constituents 47 (cellulose, hemicelluloses, and lignin) of the raw materials. Additionally, the suitability of this analytical pyrolysis 48 method under varying conditions was investigated as a rapid tool for roughly detecting chemical changes that were 49 taking place in the feedstocks during the different treatments performed.

50 Thermal analysis can be defined as a set of techniques used to describe the physical or chemical changes 51 associated with substances as a function of temperature [7]. The thermal behavior of lignocellulosic materials and 52 their components can be studied in many alternative ways. Py-GC/MS reveals the composition of products and 53 indicates the mechanisms of degradation reactions; it also provides information about the original structure of the 54 samples being studied. In general, many studies indicated that during pyrolysis under an inert atmosphere, biomass 55 converts into low-degree-polymerized products [8-17]. However, there have still been less attention on pyrolysis of 56 glucomannan and xylan as well as their quantification analyses. The dissimilarities in pyrolysis behavior of the main 57 components in lignocellulosic biomass are due to differences in their molecular structures and chemical natures. 58 Therefore, the study of pyrolysis behavior of the main biomass substituents is essential to understand the overall 59 pyrolysis behavior of biomass. In contrast, thermal gravimetric (TG) analysis (i.e., mass change vs. temperature) and 60 differential scanning calorimetry (DSC) (i.e., heat flux vs. temperature) primarily give information concerning the 61 mass loss of a sample over the whole process, the rate of mass loss, and the endothermic and exothermic 62 temperature ranges upon heating. These methods are widely applied techniques, especially for the study of thermal 63 stability of polymers. In practice, it is useful to record the first derivative of the TG curve (i.e., differential 64 thermogravimetry (DTG)) for more clearly detecting small features/boulders as peaks on the curve. Particularly, 65 successful approaches have also been the simultaneous combination of TG methods and spectroscopic techniques. In 66 general, the mass loss of a sample of the TG curve under a certain heating rate and the peak height of the DTG curve 67 are directly related to the temperature during the process and the reaction rate at the corresponding temperature, 68 respectively. Therefore, investigation of samples by TG and DTG is also important due to fluctuations in available 69 data [18-21]. 70 The cellulose content is 40-45 % of the wood dry solids and this carbohydrate is a linear homopolysaccharide 71 composed of β -D-glucopyranose moieties linked together by (1 \rightarrow 4)-glycosidic bonds (degree of polymerization 72 (DP) 10,000-15,000) [22]. Many degradation mechanisms with varying reaction kinetics of cellulose pyrolysis have 73 been proposed under changing conditions [23-32]. In the generally accepted pyrolysis reactions on heating after 74 gradual depolymerization, mainly by breaking of glycosidic linkages, a great variety of volatile products are 75 simultaneously formed (the prominent primary example is levoglucosan (LG)). This occurs from the initial 76 degradation reactions, including dehydration, rearrangement, and ring-opening of glucose units, followed by the 77 formation of various unsaturated products from which a highly reactive char can be obtained by condensation. 78 Hemicelluloses (30-35 % of the wood dry solids) are linear low-molar-mass heteropolysaccharides with specific 79 side-groups, and their thermal and chemical stability is generally lower than that of cellulose, presumably due to 80 their lack of crystallinity and lower DP (100-200) [33,34]. Softwoods and hardwoods (and non-woods) differ not 81 only in the content of total hemicelluloses but also in the percentages of individual hemicellulose constituents; in 82 hardwoods and non-woods, primarily xylan (containing xylose units), and in softwoods, mainly glucomannan 83 (containing mannose and glucose units). In hardwoods, the content of xylan and glucomannan is 20-30 % and <5 %

84 of the wood dry solids, respectively, whereas in softwoods, the corresponding contents are 5-10 % and 15-20 % of 85 the dry wood solids [33]. The thermal degradation reactions of heteropolymeric hemicelluloses are principally 86 similar to those of homopolymeric cellulose, although hemicelluloses reacted more readily than cellulose during 87 heating [13,18,34-36]. The differences observed in the degradation rates of various polysaccharides can be explained 88 as being primarily due to the different glycosidic bonds between sugar moieties as well as different DP and 89 crystallinity of cellulose. Of the hemicelluloses, xylan is the least thermally stable because it is more susceptible 90 than glucomannan to degradation of glycosidic bonds and dehydration reactions [37]. In general, the char formation 91 from hemicellulose pyrolysis is slightly higher than that from cellulose [13,14,19,38].

92 Lignin is an amorphous polymer with a chemical structure that distinctly differs from the polysaccharide 93 constituents of wood and non-wood biomass [33,39]. It is generally known that lignin decomposes over a wider 94 temperature range compared to cellulose and hemicelluloses, which are less resistant to thermal degradation and 95 rapidly degrade at lower temperatures over narrower temperature ranges [19,37,40]. Thus, the stability of lignin, 96 cellulose, and hemicelluloses against heating increases in the order: hemicelluloses > cellulose > lignin.

97 A wide range of studies has been made for clarifying the pyrolysis characteristics of varying biomasses by 98 different analytical and pilot-scale techniques [11,40-46]. Typically, it has been assumed that the pyrolysis behavior 99 of biomass is almost the integration of its components (cellulose, hemicelluloses, and lignin) [13,23], although the 100 cellulosic contribution normally predominates due to the larger proportion of cellulose in lignocellulosic materials. 101 Hence, it can be observed that with the increasing amount of hemicelluloses in the sample mixture of xylan and 102 microcrystalline cellulose, the maximum decomposition rate of hemicelluloses increases while that for cellulose 103 declines [13]. Unlike the cellulose, the interaction between hemicelluloses and lignin is strong. The presence of 104 hemicelluloses decreases the lignin decomposition temperature and the mass-loss rate, whereas the existence of 105 lignin increases the decomposition rate of hemicelluloses.

In our earlier studies, we investigated the thermochemical behavior of differently-treated wood and non-wood materials [4–6]. In this comparable study with model substances, firstly, the aim was to further clarify the formation of compound groups under the same pyrolysis conditions as those applied in our previous experiments. Secondly, to verify the formation of main pyrolysis products with respect to their main carbohydrate constituents as well as the effect of the interaction of main carbohydrate constituents in hardwood, softwood, and non-wood on the pyrolysis products. Since carbohydrates are the main components of various biorefinery fractions, we selected for our Py-GC

and TG experiments cellulose and hemicelluloses (glucomannan and xylan) and the quantification analyses of GC-

detectable pyrolysis products of these samples were reported. The thermochemical behavior of lignin as well as

114 lignin-containing black liquors from alkaline delignification of wood and non-wood fibrous feedstocks will be

separately investigated under the analogous conditions in the forthcoming studies.

116

117 **2.** Experimental

118 2.1. Thermogravimetric analyses

119 The slow pyrolysis of the selected biomass components was carried out with a Linseis STA PT1600 instrument. 120 For each test, a sample size of 10-15 mg was used in an alumina crucible. A nitrogen flow of 200 ml min⁻¹ was used 121 to create inert environment and to remove the released volatiles. For drying, the furnace temperature was raised from 122 room temperature (≈ 20 °C) to 105 °C at 20 °C min⁻¹ and maintained at that temperature for 30 min to complete the 123 drying of the sample. Then, the TG run was continued with the same dried samples for pyrolysis. The pyrolysis 124 temperature was selected as 700 °C. For pyrolysis, the sample temperature was raised from 105 °C to 700 °C at varied heating rates of 10, 15, and 20 °C min⁻¹ and maintained at that temperature for 40 min to ensure complete 125 126 pyrolysis. The data generated through TG experiments were further processed with Microsoft Excel and Matlab®.

127

128 2.2. Pyrolysis experiments

The model substances were α-cellulose (Sigma), glucomannan (MB Med. S. r. L.), and oat spelt xylan (Sigma).
In each case, about 0.2 mg of model substances was pyrolyzed in a quartz tube (3.0 cm x 1.0 mm inner diameter)
between quartz wool which was used to keep the solids inside the pyrolysis tube. First, a partly filled quartz tube
with quartz wool was cleaned at 1000 °C to remove all adsorbed gases and vapors on the surface of the quartz tube.
Then, fast pyrolysis of substances was conducted at a temperature of 500, 600, or 700 °C (heating rate 20 °C ms⁻¹
and heating times 5 and 20 s) using a CDS Pyroprobe 1000 heated filament pyrolyzer coupled to an HP 5890 II gas
chromatograph (Py-GC, Hewlett Packard Company, Wilmington, NC, USA).

136 The GC conditions were the same as those applied earlier to the similar purpose [4]. The column was a ZB-

137 35HT (Inferno) capillary GC column (30 m x 0.25 mm with a film thickness of 0.25 µm). The GC oven temperature

program in the analyses of pyrolysis products was as follows: 2 min at 40 °C, 4 °C min⁻¹ to 190 °C, 10 °C min⁻¹ to

139 320 °C, and 10 min at 320 °C. Helium was used as the carrier gas with a gas flow rate of 1 ml min⁻¹ and as an inert

140 atmosphere in the pyrolysis interface. Detection was carried out with an HP 5970 mass spectrometric detector under

electron ionization (70 eV) with 2.92 scan per seconds in the 30-550 *m/z* interval.

142 Compounds were identified using the National Institute of Standards and Technology (NIST) mass spectral

- 143 library. Quantitative analysis was conducted according to our previous study with a set of standard samples of
- 144 known concentration based on duplicated injections [4]. To utilize this, standard solutions for the low concentration
- range of 0.05-1.0 mg mL⁻¹ and for the high concentration range of 1.0-8.0 mg mL⁻¹ were prepared, depending on the
- standard's chromatographic response (GC/MS). The conditions of the GC were set to those of the Py-GC/MS. To
- 147 obtain the yields of GC-detectable products, a plot of instrument response (i.e., peak area, y-axis) vs. amount of

standard solution (µg, x-axis) was performed. Therefore, the relative mass response of a target compound compared

- to the mass of the corresponding external standard was extracted from plot and the corresponding yield
- 150 (supplementary S1-3) was calculated based on the initial sample. In addition, the quantification analyses are given in
- the supplementary data (S4).
- 152 Elemental analysis was performed with a CHNOS elemental analyzer GmbH (Vario EL III) to identify the
- 153 content of carbon, hydrogen, nitrogen, and oxygen (Table 1). The tests were conducted in duplicates.
- 154

Table 1. Elemental analysis of cellulose, glucomannan, and xylan. Numbers in parentheses are calculated for "puresubstances" without any possible side-groups.

	Component	С	Н	Ν	O ^a
	Cellulose	43.25(44.45)	6.32(6.21)	- (-)	50.43(49.34)
	Glucomannan	39.96(44.45)	6.35(6.21)	0.28(-)	53.41(49.34)
	Xylan	41.57(45.46)	6.47(6.11)	- (-)	51.96(48.43)
-					

^a Calculated by difference.

158

159 3. Results and discussion

160 *3.1. Thermogravimetric considerations*

161 The temperature at which decomposition reactions of wood occur and the changes in specimen mass associated with

the reactions can be found by thermogravimetric analysis, which exactly recorded the mass loss of the solid sample

- versus temperature/time. Traditionally, the chemical kinetic models for the biomass and its components are
- 164 proposed from the analysis of the different mass loss stages and validated through the correlation between the
- 165 predicted data and the experimental mass loss curve. According to TG the mass loss of cellulose and hemicelluloses
- typically starts at about 100 °C (i.e., due to the loss of adsorbed water). At temperatures between 100 °C and 250 °C,
- the rate of mass loss is quite slow, but above 250 °C, it increases [19]. For example, cellulose undergoes an

169 xylan, displaying clear exothermic behavior [48], the most intensive thermal degradation takes place in the 170 temperature range 200-260 °C [19,49]. 171 Figure 1 shows TG and DTG curves of cellulose, glucomannan, and xylan. The average active pyrolysis ranges of 172 290-410 °C and 230-340 °C were observed for cellulose and hemicelluloses, respectively. The higher thermal 173 stability of cellulose (glucan-based polysaccharide), compared to amorphous hemicelluloses with several types of 174 glycosidic bonds and side groups, was mainly attributed to its unbranched and ordered (i.e., highly crystalline) 175 structure [1,41,19,21,50]. Among the hemicelluloses, xylan had lower thermal stability than glucomannan. The 176 pyrolysis char yield determined was 9, 27, and 25 % of the initial mass for cellulose, glucomannan, and xylan, 177 respectively. This finding agreed well with the earlier data [19,51] and suggested more multiple reactions of 178 heterogeneous hemicelluloses and their monosaccharide moieties. According to [51], the differences in the char 179 yield between cellulose and hemicelluloses are clearly due to the somewhat different pyrolysis reaction mechanisms. 180 The DTG peak heights (wt% s⁻¹) were as follows: cellulose 0.48 at 382 °C, glucomannan 0.25 at 316 °C, and xylan 181 0.57 at 304 °C.

extensive endothermic-exothermic sequence immediately above 300 °C [20,47], and it has been reported that for





184

182

168

185 The calculated based on the Flynn-Wall-Ozawa method [52] activation energy (E_a) value as a function of fractional

186 conversion (α) for cellulose, glucomannan, and xylan is presented in Fig. 2. It could be noted that the variation in E_a

187 was slightly lower for cellulose (142-162 KJ mol⁻¹) than for glucomannan and xylan. In the literature, depending on

188 the sample origin, a variety of E_a values for cellulose have been given; for example, an average value of 109.4 KJ 189 mol⁻¹ [50]. The E_a value for glucomannan varied between 111 and 301 KJ mol⁻¹, and it gradually increased in the 190 progress of pyrolysis. However, at the end of pyrolysis ($\alpha > 0.7$), a rapid rise (i.e., from 160 to 300 KJ mol⁻¹) was 191 observed. This phenomenon has also been reported earlier by [53]. They also reported the E_a values between 181 192 and 206 KJ mol⁻¹ for glucomannan in the α range 0.1-0.75. In the case of xylan, the E_a value (168-200 KJ mol⁻¹) 193 increased until $\alpha = 0.6$, and, after this point, it started to decrease. In the previous study [54], the E_a values for xylan 194 were between 150 and 250 KJ mol⁻¹ in the temperature range 185-215 °C.

195



197 **Fig. 2**. Activation energy (E_a) as a function of fractional conversion (α) for cellulose, glucomannan, and xylan. 198

196

199 It has been reported [55] that the significant variation in the E_a value with respect to α indicates a multi-step reaction 200 mechanism. Practically, the present data suggested that cellulose degradation during pyrolysis proceeded via 201 reasonably simple and straightforward mechanisms without any significant secondary reactions. In contrast, it could 202 be concluded that, due to greater variation in the E_a values for hemicelluloses, their degradation during pyrolysis 203 took place by somewhat more complicated reaction mechanisms as already indicated by the high-char yields. The 204 thermal degradation of the polysaccharides studied occurred by versatile parallel reaction paths that were not 205 characteristically specific for certain temperature ranges. Hence, with this respect, TG, without any definite 206 detention possibilities, could not suggest distinct differences in their thermochemical degradation behavior. 207 208 209

210 3.2. Pyrolysis – gas chromatographic analyses

211 The integrated chromatographic system GC/MS applied resolved most of the low-molar-mass compounds 212 released from the model substances during pyrolysis; altogether, 42 from cellulose, 47 from glucomannan, and 41 213 from xylan were identified in conformity with pure compounds and MS library. For simplicity, the dominant GC-214 amenable pyrolysis products were classified into illustrative compound groups by the same system as that used 215 earlier for similar purposes [4,5]. It could be roughly concluded that the groups of anhydrosugar (A), 216 cyclopentenone (C), furan (F), indene (I), lactone (L), and pyrone (Y) derivatives originated from carbohydrates, 217 and those of guaiacol (G) and phenol (P) derivatives originated from lignin. The characteristic groups of naphthalene 218 (N) derivatives were obtained from extractives, whereas the groups of other aromatics, benzene (B) and linear 219 ketones (LK) derivatives, were probably formed from all the model substances; examples of a typical pyrogram 220 profile at 700 °C and 20 s, for each sample are presented in Fig. 3 and the main compounds identified are listed in 221 Table 2. Practically, pyrolysis experiments under the same conditions also led to reproducible results with 222 reasonable accuracy. During the pyrolysis, a wide range of components have been detected and the mechanisms of 223 the formation of several major products in this study are considered similar to those reported by Wang et al. [13]. It 224 was assumed that principally, the formation of each compound group occurs via characteristic mechanisms and 225 pathways. In the case of cellulose pyrolysis [15], ring-opening of glucopyranose units takes place to form open-226 chain structures, followed by dehydration and cyclization to generate 5-(hydroxymethyl)furfural (5-HMF), which 227 further converts through the elimination of the hydroxymethyl group to produce furfural, and LG is produced by the 228 cleavage of the β -(1 \rightarrow 4)-glycosidic linkage in the cellulose macromolecules, followed by an intramolecular 229 rearrangement. In the case of xylan pyrolysis Shen et al. [36] and Patwardhan et al. [51] have reported that the 230 depolymerization and ring scission of xylan form ring-opened intermediates, which further produce linear ketone 231 products, such as hydroxyacetone (via carbon chain fracture), furfural and lactones (by cyclization), and alicyclic 232 ketones, such as cyclopentenones through the combination of C=C bonds. The degradation of glycosidic linkages 233 between monomer units of glucomannan results in anhydrosugars and more stable furan rings (such as 5-HMF, 5-234 MF, and furfural) [14, 53].

235











Fig. 3. The main products formed in the pyrolysis experiments (700 °C and 20 s) with cellulose, glucomannan, and
xylan. Letters indicate compound groups to which identified products belong: A (anhydrosugar derivatives), B
(benzene derivatives), C (cyclopentenone derivatives), E (catechol derivatives), F (furan derivatives), G (guaiacol
derivatives), I (indene derivatives), L (lactone derivatives), LK (linear ketone derivatives), P (phenol derivatives), S
(curring used derivatives), and N (purpose derivatives)

243 (syringyl derivatives), and Y (pyrone derivatives).

244

Table 2. The main products formed in the pyrolysis experiments with model substances.^a

Product	RT ^b	Cellulose	Glucomannan	Xylan	Group
	/min				symbol
Anhydrosugars					А
1,4:3,6-Dianhydro-α-D-glucopyranose	24.0	+	-	-	
2,3-Anhydro-D-mannosae	24.2	+	-	-	
1,6-Anhydro-β-D-glucopyranose	34.5	+	+	+	
(levoglucosan) ^c					
Benzene derivatives					В
Toluene ^c	4.6	+	+	+	
Cyclopentenone derivatives					С
Cyclopent-2-en-1-one ^c	8.3	+	+	+	
2-Methylcyclopent-2-en-1-one ^c	10.3	-	+	+	
2-Cyclopentene-1,4-dione	11.2	+	-	+	
2-Hydroxycyclopent-2-en-1-one	11.8	+	+	+	
3-Methylcyclopentane-1,2-dione ^c	15.4	+	+	+	
Catechol derivatives					Е
2,3-Dihydroxybenzaldehyde	20.5	+	+	+	
Furan derivatives					F
Furfural (furan-2-carbaldehyde) ^c	8.0	+	+	+	
5-Methylfurfural ^c	12.8	+	+	-	
2,5-Furandicarboxaldehyde ^c	19.1	+	-	-	

5-(Hydroxymethyl)furfural ^c	24.7	+	-	-	
Guaiacol derivatives					G
2-Methoxyphenol (guaiacol) ^c	17.2	-	-	+	
2-Methoxy-4-methylphenol ^c	20.7	-	-	+	
Lactone derivatives					L
5H-Furan-2-one	12.7	+	+	+	
3-Hydroxy-2-penteno-1,5-lactone	15.0	+	-	+	
4-Hydroxy-2,5-dimethylfuran-3-one ^c	17.8	+	-	+	
1-Hydroxy-3,6-dioxabicyclo[3.2.1]octan-2-one	23.2	+	+	-	
Linear ketone derivatives					LK
Methyl acrylate	5.3	-	-	+	
1-Hydroxy-2-butanone	5.7	+	-	+	
2-Methylbut-2-enal	6.4	+	+	-	
Valeraldehyde	7.3	+	+	-	
Phenol derivatives					Р
Phenol ^c	12.9	+	+	+	
2-Methylphenol ^c	15.5	+	+	+	
4-Methylphenol ^c	16.4	+	+	+	
2,4-Dimethylphenol	18.9	+	+	+	
4-Ethenylphenol	22.1	-	-	+	
Syringol derivatives					S
2,6-Dimethoxyphenol (syringol) ^c	27.6	-	-	+	
Pyrone derivatives					Y
Pyran-2-one	14.5	+	-	-	
3-Hydroxy-2-methylpyran-4-one ^c	19.3	+	-	-	
Dihydro-6-methyl-2H-pyran-3(4H)-one	22.4	+	+	+	

^a + Indicates the presence of this compound.

^bRT refers to retention time.

^cConfirmed by pure standards.

249 Most of these pyrolysis products have been detected earlier in related studies after pyrolysis of polysaccharides-250 containing samples or polysaccharides, although in different proportions [4–6,14-17,23,29,51,56-58,60]. In our 251 previous pyrolysis studies with birch wood [4] and spruce wood [5] as well as okra and miscanthus [6], there were 252 several pyrolysis products, such as guaiacol, syringyl, naphthalene, and fatty acid derivatives, that originated from 253 lignin and extractives. However, in this back up study, guaiacol and syringyl derivatives were detected only for 254 xylan, indicating that the xylan preparation used contained some minor guaiacyl-syringyl-type lignin impurities. As 255 a typical trend, in each case, the yield of GC-detectable pyrolysis products decreased steadily toward harsher 256 pyrolysis conditions enhancing the formation of char and volatiles. Hence, the pyrolysis temperature should be 257 shortened to maximize the yield of pyrolysis products (Figs. 4-6). All the compound groups with different relative 258 formation rates were detected within the temperature range studied (500 °C, 600 °C, and 700 °C), except 259 anhydrosugar derivatives (mainly LG and levoglucosanone), which were prominently obtained only from cellulose.



263 264 Fig. 4. Effects of pyrolysis temperature and residence time on yields of main product groups from cellulose. For the letter symbols, see Fig. 3.



Fig. 5. Effects of pyrolysis temperature and residence time on yields of main product groups from glucomannan. For 269 the letter symbols, see Fig. 3.



271

Fig. 6. Effects of pyrolysis temperature and residence time on yields of main product groups from xylan. For the
letter symbols, see Fig. 3.

275 Figure 7 shows the formation examples of the selected main pyrolysis products from model substances and their 276 formation decreased at the longer holding time (20 s) and the higher reaction temperature (700 °C). It could be noted 277 that, for example, 3-hydroxy-2-penteno-1,5-lactone (lactone) was primarily formed from xylan (also partly from 278 cellulose), 5H-furan-2-one (lactone) from glucomannan (also partly from cellulose), 3-methylcyclopentane-1,2-279 dione (cyclopentenone) from glucomannan, furfural (furan) from cellulose and xylan, and 5-HMF (furan) from 280 cellulose. Based on the our previous studies [4-6], of these major pyrolysis products, especially 3-hydroxy-2-281 penteno-1,5-lactone was produced by a factor of three from hardwood [4] than from softwood [5] indicating the 282 presence of a higher portion of xylan in hardwood. However, its yield from hardwood was still less than that from 283 xylan, probably due to an effect of its integration with cellulose and lignin. In the case of 5H-furan-2-one, its 284 formation was less in spruce than pure glucomannan due to their interaction. On the other hand, it decreased in 285 delignified glucomannan-poor softwood samples even by a factor of six, and it could be claimed that this compound 286 originated from glucomannan more readily than from cellulose. A decreasing trend of LG formation in untreated and 287 treated softwood samples manifested that it was formed from both glucomannan and cellulose, but more from

- cellulose. Also 3-methylcyclopentane-1,2-dione and furfural, are prominent products from birch wood and spruce
- wood as well as non-wood [6].
- 290



291

Fig. 7. Effects of temperature and time on yields of some prominent pyrolysis products.

293

294 *3.3. Formation of pyrolysis products*

It was expected that the total amounts and the relative proportions of varying compounds and compound groups were characteristically dependent on pyrolysis conditions, although the total yield of pyrolysis products that are normally recovered and identified from laboratory-scale pyrolyzers is generally known to be low [61,62]. A great number of studies have been performed to clarify the reaction networks between the basic structural unit of cellulose, D-glucose, or β -(1 \rightarrow 4)-glycosidic bond-containing low-molar-mass model compounds (e.g., to clarify the role of the dehydration and retroaldol condensation reactions of anhydrosugars and the cleavage of glycosidic bonds) [11,46,32]. Typically, the products of cellulose pyrolysis in the classic lumped kinetic models are roughly 302 divided into gases, tar, and char, rather than utilizing the detailed compound distribution. Earlier kinetic studies have

been carried out under a variety of pyrolysis conditions, leading to somewhat conflicting data with a wide range of

kinetic parameters [37]. Hence, it can be concluded that the kinetics and elementary-reaction chemistry of

305 carbohydrate pyrolysis are still debated [29].

306 A comprehensive clarification of the myriad pyrolysis reaction routes for cellulose and hemicelluloses was

307 beyond the scope of this study. Instead, the practical aim was to clarify the chemical composition of condensable

308 liquids obtained from these feedstocks at varying temperatures for evaluating the chemical usefulness of the

309 corresponding fractions. Table 3 illustrates the relative formation of the major product groups (lactone, furan, and

310 cyclopentenone derivatives) from cellulose, glucomannan, and xylan under varying pyrolysis conditions, whereas

the corresponding formation of the minor product groups (phenolic, pyrone, and anhydrosugar derivatives) is shown

312 in Table 4.

313

Table 3. Relative proportions (%) of major product groups obtained from cellulose, glucomannan, and xylan under
 varying pyrolysis conditions. The values given in parentheses refer to yields (% of the initial feedstock dry matter).^a

Product group ^b	Cellulose	Glucomannan	Xylan
500 °C			
L	46 (1.8)	33 (1.1)	48 (2.0)
F	23 (0.8)	31 (1.0)	20 (0.8)
С	16 (0.5)	26 (0.8)	11 (0.4)
600 °C			
L	39 (1.1)	21 (1.5)	43 (1.5)
F	26 (0.7)	33 (1.1)	24 (0.8)
С	17 (0.5)	32 (1.1)	14 (0.5)
700 °C			
L	33 (0.6)	17 (0.4)	33 (0.7)
F	18 (0.4)	37 (0.9)	24 (0.7)
С	21 (0.4)	33 (0.6)	19 (0.6)

^a Data from Figs. 4-6, calculated average values for heating times of 5 and 20 s.

^b L refers to lactone derivatives, F to furan derivatives, and C to cyclopentenone derivatives.

- 318
- 319
- 320
- 321
- 322
- 323
- 324

Table 4. Relative proportions (%) of minor product groups obtained from cellulose, glucomannan, and xylan under
 varying pyrolysis conditions.^a

Product group ^b	Cellulose	Glucomannan	Xylan
500 °C			
Р	1.3	3.1	9.0
Y	6.7	2.1	2.8
А	6.7	1.8	-
600 °C			
Р	4.0	7.1	6.3
Y	5.6	2.4	4.2
А	8.5	1.5	-
700 °C			
Р	9.3	10	10
Y	5.0	2.3	5.7
А	14	12	_

327

^a Data from Figs. 4-6, calculated average values for heating times of 5 and 20 s.

328 ^b P refers to phenolic derivatives, Y to pyrone derivatives, and A to anhydrosugar derivatives.

329

330 Tables 3 and 4 indicate that no distinct compound group was selectively formed at certain temperatures and the 331 major product groups lactone, furan, and cyclopentenone derivatives accounted for 72-85% (from cellulose), 86-332 90% (from glucomannan), and 76-81% (from xylan) of the total amount of pyrolysis products determined. In 333 practice, this finding means that if a mixture of cellulose, glucomannan, and xylan with equal proportions would be 334 pyrolyzed at 500 °C, about half of the condensable liquids will consist of lactone derivatives. In the case of 335 cellulose, the proportion of lactone derivatives decreased, and that of anhydrosugar derivatives increased steadily as 336 the temperature increased. For glucomannan and xylan, the proportion of lactone derivatives also decreased and the 337 proportion of cyclopentenone derivatives was slightly depressed toward the maximum temperature. However, for all 338 model substances, no significant changes in the proportion of furan derivatives could be detected. The corresponding 339 major product groups were also prominent ones identified in our earlier pyrolysis experiments, especially at 500 °C, 340 with wood and non-wood feedstocks [4–6] existing together with the lignin-derived significant product groups, 341 guaiacol, and syringyl derivatives. Particularly in the wood pyrolysis cases, estimated in view of the present results, 342 approximate calculations suggested that the proportions of these compound groups were almost equal to the 343 expected ones. 344 345 4. Conclutions

Pyrolysis-based technologies can be described as direct thermochemical conversion methods of lignocellulosic
biomass carried out in the complete or near complete absence of an oxidizing agent (air or oxygen) typically at 500-

348 700 °C to provide complex fractions of gases, condensable liquids, and char. In many biorefinery concepts, pyrolysis
349 has been applied to prepare fuels and platform chemicals. The pyrolytic degradation of biomass is dominated by the
350 behavior of its structural components, carbohydrates (cellulose and hemicelluloses, such as glucomannan and xylan)
351 and lignin.

352 In this study, the analytical pyrolysis of cellulose, glucomannan, and xylan was carried out at 500, 600, and 700 353 °C. In each case, the condensable liquids formed were analyzed in detail and classified into several characteristic 354 compound groups. The results revealed that despite some general formation trends, due to many parallel reaction 355 paths, no compound group was selectively formed at certain temperatures, and the major product groups lactone (the 356 most prominent fraction), furan, and cyclopentenone derivatives accounted for 72-85% (from cellulose), 86-90% 357 (from glucomannan), and 76-81% (from xylan) of the total amount of pyrolysis products determined. This study also 358 confirmed by thermogravimetric analyses that within the temperature range studied, cellulose was thermally more 359 stable than the heterogeneous hemicelluloses. All these findings supported those from versatile earlier research and 360 facilitated the creation of a more coherent picture of this complicated area. These kinds of data are of practical 361 importance with respect to efforts to develop new biorefinery possibilities for renewable resources.

362

363 Acknowledgments

Financial support from the Academy of Finland, within the framework of the project IMUSTBC (Maryam Ghalibaf)is gratefully acknowledged.

366

367 References

- 368 1. Alén R. Principles of biorefining. In: Alén R, editor. Biorefining of Forest Resources. Helsinki, Finalnd: Paper
- 369 Engineers' Association; 2011. pp. 55–114.
- 2. Alén R. Pulp mills and wood-based biorefiners. In: Pandey A, Höfer R, Taherzadeh M, Nampoothiri KM,
- 371 Larroche C, editors. Industrial Biorefineries and White Biotechnology. Amsterdam, The Netherlands: Elsevier;
- **372** 2015. pp. 91–126.
- 373 3. Lehto J. Advanced Biorefinery Concepts Integrated to Chemical Pulping. Doctoral thesis. University of
- **374** Jyväskylä, Finland; 2015.
- 4. Ghalibaf M, Lehto J, Alén R. Fast pyrolysis of hot-water-extracted and delignified silver birch (*Betula pendula*)

- sawdust by Py-GC/MS. J Anal Appl Pyrolysis. 2017;127C:17–22.
- 377 5. Ghalibaf M, Lehto J, Alén R. Fast pyrolysis of hot-water-extracted and delignified Norway spruce (*Picea abies*)
- 378 sawdust by Py-GC/MS. Submitted to Wood Sci Technol. 2018.
- 379 6. Ghalibaf M, Ullah S, Alén R. Fast pyrolysis of hot-water-extracted and soda-AQ-delignified okra (Abelmoschus
- esculentus) and miscanthus (Miscanthus x giganteous) stalks by Py-GC/MS. Biomass Bioenergy. 2018;118:172-
- **381** 179.
- 382 7. Nguyen T, Zavarin E, Barrall EM. Thermal Analysis of Lignocellulosic Materials. Part I. Unmodified Materials. J
- 383 Macromol Sci Part C. 1981;20:1–65.
- 8. Banyasz JL, Li S, Lyons-Hart J, Shafer KH. Gas evolution and the mechanism of cellulose pyrolysis. Fuel.
 2001;80:1757–63.
- 386 9. Qu T, Guo W, Shen L, Xiao J, Zhao K. Experimental study of biomass pyrolysis based on three major
- 387 components: Hemicellulose, cellulose, and lignin. Ind Eng Chem Res. 2011;50:10424–33.
- 388 10. Van de Velden M, Baeyens J, Brems A, Janssens B, Dewil R. Fundamentals, kinetics and endothermicity of the
- biomass pyrolysis reaction. Renew Energy. 2010;35:232–42.
- 390 11. Wang S, Dai G, Yang H, Luo Z. Lignocellulosic biomass pyrolysis mechanism: A state-of-the-art review. Prog
- **391** Energy Combust Sci. 2017;62:33–86.
- 392 12. Meier D, Faix O. State of the art of applied fast pyrolysis of lignocellulosic materials A review. Bioresour
- **393** Technol. 1999;68:71–7.
- 13. Wang S, Luo Z. Pyrolysis of Biomass. Berlin, Germany: Walter de Gruyter GmbH; 2017.
- 395 14. Branca C, Di Blasi C, Mango C, Hrablay I. Products and kinetics of glucomannan pyrolysis. Ind Eng Chem Res.
 396 2013;52:5030–9.
- 397 15. Lu Q, Yang XC, Dong CQ, Zhang ZF, Zhang XM, Zhu XF. Influence of pyrolysis temperature and time on the
- cellulose fast pyrolysis products: Analytical Py-GC/MS study. J Anal Appl Pyrolysis. 2011;92:430–8.
- 399 16. Wang S, Guo X, Liang T, Zhou Y, Luo Z. Mechanism research on cellulose pyrolysis by Py-GC/MS and
- 400 subsequent density functional theory studies. Bioresour Technol. 2012;104:722–8.
- 401 17. Wang S, Liang T, Ru B, Guo X. Mechanism of xylan pyrolysis by Py-GC/MS. Chem Res Chinese Univ.
- **402** 2013;29:782–7.
- 403 18. Chen WH, Kuo PC. Isothermal torrefaction kinetics of hemicellulose, cellulose, lignin and xylan using

- 404 thermogravimetric analysis. Energy. 2011;36:6451–60.
- 405 19. Alén R, Rytkönen S, McKeough P. Thermogravimetric behavior of black liquors and their organic constituents.
- 406 J Anal Appl Pyrolysis. 1995;31:1–13.
- 407 20. Elder T. Pyrolysis of wood. In: Hon DN-S, Shiraishi N, editors. Wood and Cellulose Chemistry. New York, NY,
- 408 USA: Marcel Dekker; 1991. pp. 665–92.
- 409 21. Stefanidis SD, Kalogiannis KG, Iliopoulou EF, Michailof CM, Pilavachi PA, Lappas AA. A study of
- 410 lignocellulosic biomass pyrolysis via the pyrolysis of cellulose, hemicellulose and lignin. J Anal Appl Pyrolysis.
- **411** 2014;105:143–50.
- 412 22. Alén R. Cellulose derivatives. In: Alén R, editor. Biorefining of Forest Resources. Helsinki, Finland: Paper
- 413 Engineers' Association; 2011. pp. 305–54.
- 414 23. Alén R, Kuoppala E, Oesch P. Formation of the main degradation compound groups from wood and its
- 415 components during pyrolysis. J Anal Appl Pyrolysis. 1996;36:137–48.
- 416 24. Piskorz J, Radlein D, Scott DS. On the mechanism of the rapid pyrolysis of cellulose. J Anal Appl Pyrolysis.
- **417** 1986;9:121–37.
- 418 25. Scott DS, Piskorz J, Bergougnou MA, Graham R, Overend RP. The role of temperature in the fast pyrolysis of
- 419 cellulose and wood. Ind Eng Chem Res. 1988;27:8–15.
- 420 26. Radlein D, Piskorz J, Scott DS. Fast pyrolysis of natural polysaccharides as a potential industrial process. J Anal
- 421 Appl Pyrolysis. 1991;19:41–63.
- 422 27. Mamleev V, Bourbigot S, Yvon J. Kinetic analysis of the thermal decomposition of cellulose: The main step of
- 423 mass loss. J Anal Appl Pyrolysis. 2007;80:151–65.
- 424 28. Lanza R, Dalle Nogare D, Canu P. Gas phase chemistry in cellulose fast pyrolysis. Ind Eng Chem Res.
- **425** 2009;48:1391–9.
- 426 29. Lin YC, Cho J, Tompsett GA, Westmoreland PR, Huber GW. Kinetics and mechanism of cellulose pyrolysis. J
- 427 Phys Chem C. 2009;113:20097–107.
- 30. Shen D, Gu S. The mechanism for thermal decomposition of cellulose and its main products. Bioresour Technol.
 2009;100:6496–504.
- 430 31. Lédé J. Cellulose pyrolysis kinetics: An historical review on the existence and role of intermediate active
- 431 cellulose. J Anal Appl Pyrolysis. 2012;94:17–32.

- 432 32. Collard FX, Blin J. A review on pyrolysis of biomass constituents: Mechanisms and composition of the products
- 433 obtained from the conversion of cellulose, hemicelluloses and lignin. Renew Sustain Energy Rev. 2014;38:594–608.
- 434 33. Alén R. Structure and chemical composition of biomass feedstocks. In: Alén R, editor. Biorefining of Forest
- 435 Resources. Helsinki, Finland: Paper Engineers' Association; 2011. pp. 17–54.
- 436 34. Zhou X, Li W, Mabon R, Broadbelt LJ. A Critical review on hemicellulose pyrolysis. Energy Technol.
- **437** 2017;5:52–79.
- 438 35. Shafizadeh F, McGinnis GD, Philpot CW. Thermal degradation of xylan and related model compounds.
- **439** Carbohydr Res. 1972;25:23–33.
- 440 36. Shen D, Gu S, Bridgwater A V. Study on the pyrolytic behaviour of xylan-based hemicellulose using TG-FTIR
- 441 and Py-GC-FTIR. J Anal Appl Pyrolysis. 2010;87:199–206.
- 442 37. Balat M. Mechanisms of thermochemical biomass conversion processes. Part 1: Reactions of pyrolysis. Energ
- 443 Sources, Part A: Recovery, Utilization and Environmental Effects. 2008;30:620–35.
- 444 38. Di Blasi C, Lanzetta M. Intrinsic kinetics of isothermal xylan degradation in inert atmosphere. J Anal Appl
- 445 Pyrolysis. 1997;40–41:287–303.
- 446 39. Tian X, Fang Z, Smith RL, Wu Z, Liu M. Properties, chemical characteristics and application of lignin and its
- derivatives. In: Fang Z, Smith RL, editors. Production of Biofuels and Chemicals from Lignin. Singapore: Springer
- 448 Science+Business Media Singapore; 2016. pp. 3–33.
- 449 40. Dhyani V, Bhaskar T. A comprehensive review on the pyrolysis of lignocellulosic biomass. Renew Energy.
- **450** 2017;1–22.
- 41. Bridgwater AV, Meier D, Radlein D. An overview of fast pyrolysis of biomass. Org geochemistry J.
- **452** 1999;30:1479–93.
- 453 42. Yang H, Yan R, Chen H, Lee DH, Zheng C. Characteristics of hemicellulose, cellulose and lignin pyrolysis.
- 454 Fuel. 2007;86:1781–8.
- 43. Bridgwater AV. Review of fast pyrolysis of biomass and product upgrading. Biomass and Bioenergy.
- 456 2012;38:68–94.
- 457 44. Várhegyi G, Antal MJ, Jakab E, Szabó P. Kinetic modeling of biomass pyrolysis. J Anal Appl Pyrolysis.
- **458** 1997;42:73–87.
- 45. Faix O, Fortmann I, Bremer J, Meier D. Thermal degradation products of wood: Gas chromatographic separation

- and mass spectrometric characterization of polysaccharide derived products. Eur J Wood Wood Prod. 1991;49:213–
 9.
- 46. White JE, Catallo WJ, Legendre BL. Biomass pyrolysis kinetics: A comparative critical review with relevant

463 agricultural residue case studies. J Anal Appl Pyrolysis. 2011;91:1–33.

- 464 47. Williams PT, Besler S. Thermogravimetric analysis of components of biomass. In: Bridgwater AV, editor.
- 465 Advances in Thermochemical Biomass Conversion, Vol 2, Pyrolysis. Dordrecht, The Netherlands: Springer; 1993.
- 466 pp. 771–83.
- 467 48. Werner K, Pommer L, Broström M. Thermal decomposition of hemicelluloses. J Anal Appl Pyrolysis.
 468 2014:110:130–7.
- 469 49. Parker WJ, Levan SL. kinetic properties of the components of Douglas-fir and the heat of combustion of their
- 470 volatile pyrolysis products. Wood Fiber Sci. 1989;21:289–305.
- 471 50. Wang S, Lin H, Ru B, Dai G, Wang X, Xiao G, et al. Kinetic modeling of biomass components pyrolysis using a
- 472 sequential and coupling method. Fuel. 2016;185:763–71.
- 473 51. Patwardhan PR, Brown RC, Shanks BH. Product distribution from the fast pyrolysis of hemicellulose. Chem
- 474 Sustain energy Mater. 2011;4:636–43.
- 475 52. Doddapaneni TRKC, Konttinen J, Hukka TI, Moilanen A. Influence of torrefaction pretreatment on the pyrolysis
- 476 of Eucalyptus clone: A study on kinetics, reaction mechanism and heat flow. Ind Crops Prod. 2016;92:244–54.
- 477 53. Moriana R, Zhang Y, Mischnick P, Li J, Ek M. Thermal degradation behavior and kinetic analysis of spruce
- 478 glucomannan and its methylated derivatives. Carbohydr Polym. 2014;106:60–70.
- 479 54. Jin W, Singh K, Zondlo J. Pyrolysis Kinetics of Physical Components of Wood and Wood-Polymers Using
- 480 Isoconversion Method. Agriculture. 2013;3:12–32.
- 481 55. Janković B, Adnadević B, Jovanović J. Application of model-fitting and model-free kinetics to the study of non-
- 482 isothermal dehydration of equilibrium swollen poly (acrylic acid) hydrogel: Thermogravimetric analysis.
- 483 Thermochim Acta. 2007;452:106–15.
- 56. Evans RJ, Milne TA. Molecular characterization of pyrolysis of biomass. 1. Fundamentals. Energy Fuels.
 1987;1:123–38.
- 486 57. Räisänen U, Pitkänen I, Halttunen H, Hurtta M. Formation of the main degradation compounds from arabinose,
- 487 xylose, mannose and arabinitol during pyrolysis. J Therm Anal Calorim. 2003;72:481–8.

- 488 58. Nowakowski DJ, Jones JM. Uncatalysed and potassium-catalysed pyrolysis of the cell-wall constituents of
- 489 biomass and their model compounds. J Anal Appl Pyrolysis. 2008;83:12–25.
- 490 59. Patwardhan PR, Dalluge DL, Shanks BH, Brown RC. Distinguishing primary and secondary reactions of
- 491 cellulose pyrolysis. Bioresour Technol. 2011;102:5265–9.
- 492 60. Liaw SS, Haber Perez V, Zhou S, Rodriguez-Justo O, Garcia-Perez M. Py-GC/MS studies and principal
- 493 component analysis to evaluate the impact of feedstock and temperature on the distribution of products during fast
- 494 pyrolysis. J Anal Appl Pyrolysis. 2014;109:140–51.
- 495 61. Custodis V, Hemberger P, Ma Z, van Bokhoven J. Mechanism of pyrolysis of lignin: Studing model compounds.
- 496 J Phys Chem B. 2014;118:8524–31.
- 497 62. Lappi H. Production of Hydrocarbon-rich Biofuels from Extractives-derived Materials. Doctoral thesis.
- 498 University of Jyväskylä, Finland; 2012.

Supplementary data S1: Yield of cellulose pyrolysis products (%)

Pyrolysis products	RT ^a	500 °C.	500 °C.	600 °C.	600 °C.	700 °C.	700 °C.
- JJ	/min	5 s	20 s	5 s	20 s	5 s	20 s
Toluene	4.6	-	-	-	0.02	0.02	0.04
2-Methylbut-2-enal	6.4	0.32	0.36	-	0.08	-	-
Furfural	8.0	0.28	0.34	0.28	0.26	0.22	0.18
Cyclopent-2-en-1-one	8.1	0.06	0.08	0.06	0.08	0.08	0.08
Furanmethanol	8.2	-	-	0.04	-	-	
Ethenylbenzene	8.3	-	-	-	-	0.02	0.02
5-Methyl-3 <i>H</i> -furan-2-one	9.1	0.1	0.1	-	-	-	-
1-Acetoxypropan-2-one	9.3	0.12	-	0.28	-	-	-
Cyclohexanone	9.7	0.02	0.04	0.02	0.02	-	-
2-Methylcyclopent-2-en-1-one	10.3	0.02	-	0.06	-	0.04	0.04
1-(2-Furvl)ethanone	10.4	-	-	0.04	0.01	-	-
2-Cyclopenten-1.4-dione	11.2	-	0.06	0.02	0.04	0.02	0.02
2-Hydroxycyclopent-2-en-1-one	11.6	0.16	0.22	0.2	0.14	0.14	0.1
5 <i>H</i> -Furan-2-one	12.5	0.46	0.32	0.34	0.22	0.1	0.1
Phenol	12.7	0.04	0.04	0.04	0.06	0.06	0.1
5-Methylfurfural	12.7	0.02	0.12	0.04	0.06	0.06	0.06
Pyran-2-one	14.2	-	-	-	0.06	0.06	0.06
3-Methyl-5 <i>H</i> -furan-2-one	14.4	0.06	0.1	0.1	0.1	0.22	-
1 <i>H</i> -Indene	14.5	-	-	-	-	-	0.02
2H-Pyran-2 6(3H)-dione	14.6	0.14	-	-	_	-	-
3-Hydroxy-2-penteno-1 5-lactone	15.0	0.58	0.72	0.52	0.34	03	0.24
3-Methylcyclopentane-1,2-dione	15.4	0.2	0.26	0.2	0.12	0.12	0.1
2-Methylphenol	15.5	-	-	-	0.02	0.02	0.02
4-Methylphenol	16.4	-	0.02	0.02	0.02	0.04	0.02
4-Methyl-5 <i>H</i> -furan-2-one	17.9	0.1	0.02	0.02	0.0	0.01	-
4-Hydroxy-2.5-dimethylfuran-3-one	18.1	0.06	0.08	0.06	0.04	0.02	-
Methylfuran-2-carboxylate	18.1	0.08	0.08	0.06	0.06	0.04	-
1-Methyl-1 <i>H</i> -indene	18.3	-	-	-	-	-	0.02
2-Hydroxy-3-ethylcyclopent-2-en-1-one	18.5	-	-	0.02	_	-	-
2.4-Dimethylphenol	18.9	-	-	0.02	0.02	0.02	0.02
3-Hydroxy-2-methylpyran-4-one	19.0	0.1	0.1	0.08	-	-	-
2.5-Furandicarboxaldehyde	19.1	-	-	0.16	0.16	-	-
Levoglucosenone	19.8	0.03	0.03	0.03	0.03	0.03	0.03
Naphthalene	20.4	-	-	-	-	-	0.02
2.3-Dihydroxybenzaldehyde	20.5	0.1	0.1	0.1	_	-	-
3 5-Dihydroxy-2-methylpyran-4-one	21.5	-	0.08	-	_	-	-
Dihydro-6-methyl-2 <i>H</i> -pyran-3(4 <i>H</i>)-one	22.4	0.12	0.00	0.12	0.1	0.1	0.08
(1R 5S)-1-Hydroxy-3 6-	23.0	0.16	0.18	0.12	0.12	0.12	0.06
dioxabicyclo[3 2 1]octan-2-one	23.0	0.10	0.10	0.12	0.12	0.12	0.00
1 4.3 6-Dianhydro- <i>a</i> -D-glucopyranose	23.8	0.06	0.06	0.06	0.06	0.06	0.06
2.3-Anhydro-D-mannose	24.2	0.06	0.08	0.06	0.06	0.06	0.04
5-(Hydroxymethyl)furfural	24.6	0.1	0.1	0.06	0.06	0.04	0.04
2.3-Dihydro-1 <i>H</i> -indene-1-one	25.4	-	-	-	0.02	-	-
Levoglucosan	34.5	0.1	0.1	0.1	0.12	0.14	0.12
Leveglueosuli	54.5	0.1	0.1	0.1	0.12	0.14	0.12

^a RT refers to retention time (min).

Supplementary data S2: Yield of glucomannan pyrolysis products (%)

Pyrolysis products	RTa	500 °C	500 °C	600 °C	600 °C	700 °C	700 °C
	/min	5 s	20 s	5 s	20 s	5 s	20 s
Toluene	4.6	0.02	0.02	0.04	0.02	0.02	0.04
2-Methylbut-2-enal	6.4	0.02	0.02	0.76	0.8	-	-
1 2-Dimethylbenzene	7.2	-	-	-	-	_	0.02
Pentanal	7.2	3.92	2.96	3.48	2.88	2 44	2.68
Furfural	7.9	0.1	0.12	0.18	0.12	0.12	0.14
Cyclopent-2-en-1-one	8.1	0.06	0.12	0.10	0.12	0.08	0.14
Europent-2-en-1-one	8.2	0.00	0.1	0.12	0.12	0.00	0.1
5 Mothyl 3H furan 2 ono	0.2	0.22	0.22	0.40	0.12	0.00	0.10
1 Acotovy propen 2 one	0.3	0.1	0.1	-	- 0.2	- 0.16	-
Cuelebevenene	9.5	0.4	0.12	-	0.2	0.10	0.2
2 Mathylayalopant 2 on 1 one	9.7	0.02	0.02	0.04	-	-	-
2-Methylcyclopent-2-en-1-one	10.5	0.04	0.00	0.06	0.00	0.04	0.00
2 Cueleperter 1.4 diana	10.4	0.04	0.03	0.00	0.05	0.04	0.03
2-Cyclopenten-1,4-dione	11.2	0.04	0.04	0.00	0.04	0.02	0.02
2-Hydroxycyclopent-2-en-1-one	11.0	0.18	0.18	0.24	0.18	0.12	0.14
2-Methylethenylbenzene	12.2	-	-	-	-	-	0.02
SH-Furan-2-one	12.7	0.62	0.66	0.54	0.34	0.22	0.2
	12.8	0.02	0.08	0.1	0.1	0.08	0.12
5-Methylfurfural	12.8	0.02	-	-	0.08	0.08	0.1
5-Methyl-5 <i>H</i> -turan-2-one	12.9	0.06	0.1	-	-	-	-
3-Methylcyclopent-2-en-1-one	13.1	0.04	0.06	0.08	0.08	0.04	0.06
2,3-Dimethylcyclopent-2-en-1-one	13.4	-	0.02	0.04	0.04	-	0.02
3-Methyl-5 <i>H</i> -furan-2-one	14.4	0.12	-	0.1	0.1	0.1	-
1 <i>H</i> -Indene	14.5	-	-	-	-	-	0.02
2,3-dimethylcyclopent-2-en-1-one	14.8	0.1	0.12	0.12	0.1	-	-
3-Methylcyclopentane-1,2-dione	15.4	0.28	0.28	0.4	0.3	0.2	0.32
2-Methylphenol	15.5	-	0.02	0.02	0.02	0.04	0.04
2-Hydroxy-3,5-dimethylcyclopent-2-en-	15.6	0.02	0.02	0.06	0.04	0.02	0.06
1-one							
4-Methylphenol	16.4	0.02	0.04	0.06	0.08	0.06	0.1
2-Methoxyphenol	17.2	0.04	0.04	-	-	-	-
3-Ethylcyclopent-2-en-1-one	17.2	-	-	0.04	0.02	0.02	-
2,6-Dimethylphenol	17.4	-	-	0.02	0.02	-	0.02
4-Methyl-5 <i>H</i> -furan-2-one	17.6	0.1	0.1	0.12	0.1	0.1	0.1
4-Hydroxy-2,5-dimethylfuran-3-one	17.6	-	0.04	0.04	-	-	-
Methylfuran-2-carboxylate	17.7	0.06	0.06	0.08	0.06	-	0.06
2-Hydroxy-3-ethylcyclopent-2-en-1-one	18.3	0.06	0.14	0.14	0.12	0.1	0.14
1-Methyl-1 <i>H</i> -indene	18.6	-	-	-	-	-	0.02
2,4-Dimethylphenol	18.9	0.02	0.02	0.04	0.02	0.02	0.04
3-Ethylphenol	19.6	-	-	-	-	-	0.04
3,5-Dimethylphenol	20.1	-	-	0.02	0.02	0.02	0.02
Naphthalene	20.5	-	-	-	-	-	0.02
2,3-Dihydroxybenzaldehyde	20.5	0.1	0.1	0.1	0.08	-	-
1,2-Dihydroxybenzene	21.7	-	-	-	-	-	0.06
Dihydro-6-methyl-2 <i>H</i> -pyran-3(4 <i>H</i>)-one	22.2	0.06	0.08	0.08	0.08	0.08	-
(1 <i>R</i> ,5 <i>S</i>)-1-Hydroxy-3.6-	23.0	0.04	0.04	0.04	0.04	0.04	0.04
dioxabicyclo[3.2.1]octan-2-one							
1-Methylnaphthalene	24.3	-	-	-	-	-	0.02
4-Ethyl-2-methoxyphenol	24.3	-	-	0.04	-	-	-
Levoglucosan	34.5	0.05	0.07	0.05	0.05	0.03	0.03
00							

^a RT refers to retention time (min).

Supplementary data S3: Yield of xylan pyrolysis products (%)

$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$	Pyrolysis products	RT ^a	500 °C,	500 °C,	600 °C,	600 °C,	700 °C,	700 °C,
		/min	5 s	20 s	5 s	20 s	5 s	20 s
Methyl prop-2-enoate 5.3 3.26 4.16 2.42 1.94 1.28 1.52 1-Hydroxybutan-2-one 5.7 1.16 1.00 1.48 1.00 1.04 1.00 Purfural 8.0 0.32 0.48 0.4 0.44 0.42 0.32 0.34 Cyclopent-2-en-1-one 8.1 - - - - 0.02 0.04 Furamethanol 8.6 0.06 0.02 0.06 0.02 - - 5.Methyl-3H-furan-2-one 9.1 0.1 0.1 0.06 0.02 0.14 0.16 0.12 </td <td>Toluene</td> <td>4.6</td> <td>0.01</td> <td>0.01</td> <td>0.02</td> <td>0.02</td> <td>0.04</td> <td>0.04</td>	Toluene	4.6	0.01	0.01	0.02	0.02	0.04	0.04
1-Hydroxybutan-2-one 5.7 1.16 1.00 1.48 1.00 1.04 1.00 1,2-Dimethylbenzene 7.2 - - - - 0.02 Furfural 8.0 0.32 0.48 0.44 0.32 0.34 Cyclopent-2-en-1-one 8.1 - 0.08 0.08 0.08 0.08 0.08 Ethenylbenzene 8.4 - - - - 0.02 0.04 0.04 0.02 - - I-Meteoxy-propan-2-one 9.1 0.1 0.1 0.06 0.01 - - - - - - - - - - - - - - - - 0.02 0.04 0.02 0.04 0.02 0.	Methyl prop-2-enoate	5.3	3.26	4.16	2.42	1.94	1.28	1.52
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	1-Hydroxybutan-2-one	5.7	1.16	1.00	1.48	1.00	1.04	1.00
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	1,2-Dimethylbenzene	7.2	-	-	-	-	-	0.02
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	Furfural	8.0	0.32	0.48	0.4	0.44	0.32	0.34
Ethenylbenzene 8.4 - - - - 0.02 0.04 Furanmethanol 8.6 0.06 0.02 - - - 5-Methyl-3H-furan-2-one 9.1 0.1 0.02	Cyclopent-2-en-1-one	8.1	-	0.08	0.08	0.08	0.08	0.08
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	Ethenylbenzene	8.4	-	-	-	-	0.02	0.04
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	Furanmethanol	8.6	0.06	0.02	0.06	0.02	-	-
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	5-Methyl-3 <i>H</i> -furan-2-one	9.1	0.1	0.1	0.06	0.1	-	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	1-Acetoxy-propan-2-one	9.3	0.12	0.2	0.36	0.24	0.16	0.24
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	Cyclohexanone	9.7	-	0.02	0.02	0.02	0.02	0.02
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	2-Methylcyclopent-2-en-1-one	10.3	0.1	0.08	0.1	0.08	0.06	0.06
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	2-Cyclopenten-1,4-dione	11.2	0.02	0.02	0.04	0.02	0.02	0.02
	2-Hydroxycyclopent-2-en-1-one	11.6	0.08	0.12	0.14	0.12	0.14	0.12
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	5H-Furan-2-one	12.5	0.18	0.2	0.28	0.14	0.16	0.12
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	Phenol	12.9	0.28	0.28	0.08	0.1	0.1	0.16
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	3-Methylcyclopent-2-en-1-one	13.1	0.02	0.04	0.04	0.04	0.02	0.02
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	3-Hydroxy-2-penteno-1,5-lactone	15.0	1.52	1.8	1.22	1.22	0.72	0.9
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	3-Methylcyclopentane-1,2-dione	15.4	0.1	0.14	0.16	0.12	0.12	0.14
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	2-Methylphenol	15.5	-	-	0.02	0.02	0.02	0.02
en-1-one16.40.020.040.040.060.060.082-Methoxyphenol17.20.040.060.040.040.040.044-Methyl-5H-furan-2-one17.90.040.040.040.020.020.024-Hydroxy-2,5-dimethylfuran-3-one18.10.020.040.040.020.020.022-Hydroxy-3-ethylcyclopent-2-en-1-18.30.020.060.060.060.060.082,4-Dimethylphenol18.9-0.020.020.020.020.022-Ethylphenol19.60.040.040.020.020.020.022,3-Dihydroxybenzaldehyde20.50.120.120.120.120.120.122-Methoxy-4-methylphenol20.70.040.040.020.020.041,2-Dihydroxybenzene21.50.042,5'-Dihydroxybenzene22.10.020.020.020.020.040.160.160.160.160.160.160.160.923.40.080.10.080.082',5'-Dihydroxyacetophenone23.70.022-Methoxy-4-ethylphenol23.50.040.040.020.021.2-Dihydroxy-3-methylbenzene23.70.022-Methoxy-4-ethylphenol25.40.060.060.040.04 <t< td=""><td>2-Hydroxy-3,5-dimethylcyclopent-2-</td><td>15.6</td><td>0.02</td><td>0.02</td><td>0.02</td><td>-</td><td>-</td><td>-</td></t<>	2-Hydroxy-3,5-dimethylcyclopent-2-	15.6	0.02	0.02	0.02	-	-	-
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	en-1-one							
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	4-Methylphenol	16.4	0.02	0.04	0.04	0.06	0.06	0.08
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	2-Methoxyphenol	17.2	0.04	0.06	0.04	0.04	0.04	0.04
4-Hydroxy-2,5-dimethylfuran-3-one18.1 0.02 0.04 0.04 0.02 0.02 0.02 2-Hydroxy-3-ethylcyclopent-2-en-1- one18.3 0.02 0.06 0.06 0.06 0.06 0.06 2,4-Dimethylphenol18.9- 0.02 0.02 0.02 0.02 0.02 2-Ethylphenol19.6 0.04 0.04 0.02 0.04 0.02 0.02 2,3-Dihydroxybenzaldehyde20.5 0.12 0.12 0.12 0.12 0.12 2-Methoxy-4-methylphenol20.7 0.04 0.04 0.04 0.02 0.04 1,2-Dihydroxybenzene21.50.024-Ethenylphenol22.1 0.02 0.02 0.02 0.02 0.04 0.120.12 0.12 0.16 0.14 0.16 0.16 0.160.12 0.12 0.12 0.12 0.12 0.12 1,2-Dihydroxyacetophenone23.4 0.08 0.1 0.08 0.08 -2',5'-Dihydroxy-3-methylbenzene23.70.021,2-Dihydroxy-3-methylbenzene23.70.021-Methylnaphthalene24.20.021-Methylnaphthalene24.20.021-Methylnaphthalene25.4 0.06 0.06 0.04 0.04 0.04 1-Methylnaphthalene27.6 0.04 <t< td=""><td>4-Methyl-5<i>H</i>-furan-2-one</td><td>17.9</td><td>0.04</td><td>0.04</td><td>0.04</td><td>0.02</td><td>0.02</td><td>0.02</td></t<>	4-Methyl-5 <i>H</i> -furan-2-one	17.9	0.04	0.04	0.04	0.02	0.02	0.02
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	4-Hydroxy-2,5-dimethylfuran-3-one	18.1	0.02	0.04	0.04	0.02	0.02	0.02
one18.9-0.020.020.020.020.022-Ethylphenol19.60.040.040.020.040.020.022.3-Dihydroxybenzaldehyde20.50.120.120.120.120.110.122-Methoxy-4-methylphenol20.70.040.040.040.020.040.041,2-Dihydroxybenzene21.50.044-Ethenylphenol22.10.020.020.020.020.04Dihydro-6-methyl-2H-pyran-3(4H)-22.40.120.120.160.140.16one23.40.080.10.080.082-Methoxy-4-ethylphenol23.50.040.040.020.021,2-Dihydroxyacetophenone23.70.08-1-Methylnaphthalene24.20.020.024-Ethenyl-2-methoxyphenol25.40.060.060.040.040.040.042,6-Dimethoxyphenol27.60.040.040.040.020.020.020.02Levoglucosan34.50.160.10.080.080.040.020.02Dibutyl benzene-1,2-dicarboxylate42.30.020.02	2-Hydroxy-3-ethylcyclopent-2-en-1-	18.3	0.02	0.06	0.06	0.06	0.06	0.08
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	one							
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	2,4-Dimethylphenol	18.9	-	0.02	0.02	0.02	0.02	0.02
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	2-Ethylphenol	19.6	0.04	0.04	0.02	0.04	0.02	0.02
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	2,3-Dihydroxybenzaldehyde	20.5	0.12	0.12	0.12	0.12	0.1	0.12
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	2-Methoxy-4-methylphenol	20.7	0.04	0.04	0.04	0.02	0.04	0.04
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	1,2-Dihydroxybenzene	21.5	-	-	-	-	-	0.04
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	4-Ethenylphenol	22.1	0.02	0.02	0.02	0.02	0.02	0.04
one 23.4 0.08 0.1 0.08 0.08 - - 2-Methoxy-4-ethylphenol 23.5 0.04 0.04 0.02 0.02 - - 1,2-Dihydroxy-3-methylbenzene 23.7 - - - 0.08 1-Methylnaphthalene 24.2 - - - 0.02 4-Ethenyl-2-methoxyphenol 25.4 0.06 0.06 0.04 0.04 0.02 2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 - - - -	Dihydro-6-methyl-2 <i>H</i> -pyran-3(4 <i>H</i>)-	22.4	0.12	0.12	0.16	0.14	0.16	0.16
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	one							
2-Methoxy-4-ethylphenol 23.5 0.04 0.04 0.02 0.02 - - 1,2-Dihydroxy-3-methylbenzene 23.7 - - - - 0.08 1-Methylnaphthalene 24.2 - - - - 0.02 4-Ethenyl-2-methoxyphenol 25.4 0.06 0.06 0.04 0.04 0.04 2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 - - - -	2',5'-Dihydroxyacetophenone	23.4	0.08	0.1	0.08	0.08	-	-
1,2-Dihydroxy-3-methylbenzene 23.7 - - - - 0.08 1-Methylnaphthalene 24.2 - - - - 0.02 4-Ethenyl-2-methoxyphenol 25.4 0.06 0.06 0.04 0.04 0.04 2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - - - -	2-Methoxy-4-ethylphenol	23.5	0.04	0.04	0.02	0.02	-	-
1-Methylnaphthalene 24.2 - - - - 0.02 4-Ethenyl-2-methoxyphenol 25.4 0.06 0.06 0.06 0.04 0.04 0.04 2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - - -	1,2-Dihydroxy-3-methylbenzene	23.7	-	-	-	-	-	0.08
4-Ethenyl-2-methoxyphenol 25.4 0.06 0.06 0.04 0.04 0.04 2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - - -	1-Methylnaphthalene	24.2	-	-	-	-	-	0.02
2,6-Dimethoxyphenol 27.6 0.04 0.04 0.04 0.02 0.02 Levoglucosan 34.5 0.16 0.1 0.08 0.04 0.02 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - - - -	4-Ethenyl-2-methoxyphenol	25.4	0.06	0.06	0.06	0.04	0.04	0.04
Levoglucosan 34.5 0.16 0.1 0.08 0.08 0.04 0.02 Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - - - -	2,6-Dimethoxyphenol	27.6	0.04	0.04	0.04	0.04	0.02	0.02
Dibutyl benzene-1,2-dicarboxylate 42.3 0.02 0.02 - <td>Levoglucosan</td> <td>34.5</td> <td>0.16</td> <td>0.1</td> <td>0.08</td> <td>0.08</td> <td>0.04</td> <td>0.02</td>	Levoglucosan	34.5	0.16	0.1	0.08	0.08	0.04	0.02
	Dibutyl benzene-1,2-dicarboxylate	42.3	0.02	0.02	-	-	-	-

^a RT refers to retention time (min).

Compound	RT ^a	Major ion(s)	Quantification ^b	r^2	Slope
L	/min	(m/z)		Value ^c	1
Linear ketones, acids, esters der	ivatives	(<c5)< td=""><td>•</td><td>-</td><td></td></c5)<>	•	-	
Acetic acid	3.7	43,60	Standard	0.96	4.1
Butanal	3.9	57,72	Standard	0.99	4.1
Methyl acrylate	5.3	55,86	Acetic acid		
1-Hydroxy-2-butanone	5.7	57, 88	Butanal		
2-Methylbut-2-enal	6.4	55, 84	Butanal		
Pentanal	7.2	58.86	Butanal		
1-Acetoxypropan-2-one	9.3	57.86.116	Acetic acid		
Benzene derivatives			1		1
Toluene	4.6	51, 65, 91	Standard	0.99	298.5
1.2-Dimethylbenzene	7.3	91, 106	Standard	0.99	230.0
Ethenylbenzene	8.4	78, 104	Standard	0.96	191.7
Furan derivatives	011	, 0, 101	Standard	0120	17117
Furfural (furan-2-carbaldehyde)	8.0	39 95 96	Standard	0.99	42.9
Furanmethanol ((furan-2-	8.6	53 69 81 98	Standard	0.99	94.2
vl)methanol)	0.0	55, 67, 61, 76	Standard	0.77	74.2
1-(2-Furyl)ethanone	10.5	95 110	5-Methylfurfural	-	
5-Methylfurfural	12.8	53 109 110	Standard	0.98	62.2
Methyl furan-2-carboxylate	18.1	39 95 126	Furfural (furan-2-	0.70	02.2
Wedly Fulur 2 eurooxylate	10.1	55, 55, 120	carbaldebyde)		
4-Hydroxy-2 5-dimethylfuran-3-	18.1	43 57 85	Standard	0.99	41.6
one	10.1	128	Standard	0.77	41.0
2 5-Furandicarboxaldebyde	19.1	53 67 95	Standard	0.99	83.0
2,5 Turandrear boxarden yde	17.1	124	Standard	0.77	05.0
5-(Hydroxymethyl)furfural	24.7	39 97 109	Standard	0.97	73.0
	2	126	Standard	0.77	/5.0
Lactone derivatives		120		1	
5-Methyl-3 <i>H</i> -furan-2-one	9.1	55, 70, 98	Standard	0.99	56.0
5 <i>H</i> -Furan-2-one	12.7	39 55 84	Standard	0.99	24.8
3-Methyl-5 <i>H</i> -furan-2-one	14.5	69.98	5-Methyl-3 <i>H</i> -furan-2-one	0.77	
3-Hydroxy-2-penteno-1 5-	15.0	58 85 114	4-Hydroxy-5-methylfuran-3-	0.97	35.2
lactone	1010	00,00,11	one	0.57	00.2
4-Methyl-5 <i>H</i> -furan-2-one	17.9	69, 98	5-Methyl-3 <i>H</i> -furan-2-one	1	
(1R 5S)-1-Hydroxy-3 6-	23.2	57 69 85	4-Hydroxy-2.5-		
dioxabicyclo[3.2.1]octan-2-one	2012	116.144	dimethylfuran-3-one		
Cyclopentenone derivatives	1			4	1
Cyclopent-2-en-1-one	8.3	39.82	Standard	0.98	118.4
Cyclohexanone	9.9	55, 69, 98	Standard	0.99	51.2
2-Methylcyclopent-2-en-1-one	10.3	53, 67, 96	Standard	0.99	65.2
2-Cyclopenten-1 4-dione	11.2	54 68 98	2-Methylcyclopent-2-en-1-	0.55	00.2
	11.2	5 1, 00, 70	one		
2-Hydroxycyclopent-2-en-1-one	11.8	55, 69, 98	2-Methylcyclopent-2-en-1-	1	
	1110	,,	one		
3-Methylcyclopent-2-en-1-one	13.3	53, 67, 96	2-Methylcyclopent-2-en-1-	1	
5 meanyreyerspent 2 en 1 one	15.5	55, 67, 76	one		
2.3-Dimethylcyclopent-2-en-1-	14.8	67 82 95	2-Methylcyclopent-2-en-1-	-	
one	1.110	110	one		
3-Methylcyclopentane-1.2-dione	15.4	55, 69, 83.	Standard	0.98	43.6
		112			
2-Hydroxy-3.5-	15.6	69, 83, 97.	2-Methylcyclopent-2-en-1-	1	1
dimethylcyclopent-2-en-1-one		111.126	one		
3-Ethylcyclopent-2-en-1-one	17.2	67, 81, 95.	2-Methylcvclopent-2-en-1-	1	1
		110	one		

Supplementary data S4: Classification of pyrolysis products including peak identification and calibration information

2-Hydroxy-3-ethylcyclopent-2-	18.5	55, 69, 83,	2-Methylcyclopent-2-en-1-		
en-1-one		126	one		
Phenol derivatives					
Phenol	12.9	66, 94	Standard	0.98	55.1
2-Methylphenol	15.5	39, 51, 79, 107	Standard	0.99	85.0
4-Methylphenol	16.4	39, 51, 79, 108	Standard	0.99	82.0
2.6-Dimethylphenol	17.4	77.107.122	Standard	0.98	128.6
2-Ethylphenol	18.3	63, 77, 107, 122	2,6-Dimethylphenol		
2,4-Dimethylphenol	18.9	65, 77, 107, 122	2,6-Dimethylphenol		
3-Ethylphenol	19.6	77, 107, 122	3,5-Dimethylphenol		
3,5-Dimethylphenol	19.8	77, 107, 122	Standard	0.98	87.6
2,3,6-Trimethylphenol	22.0	77, 91, 121, 136	Standard	0.98	222.0
4-Ethenylphenol	22.1	65, 91, 120	3,4-Dimethylphenol		
Pyran derivatives					
Pyran-2-one	14.3	39, 68, 96	3-Hydroxy-2-methylpyran-4- one		
2H-Pyran-2,6(3H)-dione	14.8	55, 84, 112	3-Hydroxy-2-methylpyran-4- one		
3-Hydroxy-2-methylpyran-4-one	19.0	43, 55, 71, 126	Standard	0.98	74.5
3,5-Dihydroxy-2-methylpyran- 4-one	21.8	68, 85, 113, 142	3-Hydroxy-2-methylpyran-4- one		
Dihydro-6-methyl-2 <i>H</i> -pyran- 3(4 <i>H</i>)-one	22.4	56, 84, 114	3-Hydroxy-2-methylpyran-4- one		
Indene derivatives	_			_	
1 <i>H</i> -Indene	14.5	63, 89, 116	Standard	0.99	211.2
1-Methyl-1 <i>H</i> -indene	18.4	115, 130	1 <i>H</i> -Indene		
2,3-Dihydro-1 <i>H</i> -indene-1-one	25.6	78, 104, 132	1 <i>H</i> -Indene		
Guaiacol derivatives					
2-Methoxyphenol (guaiacol)	17.2	53, 81, 109, 124	Standard	0.99	79.2
2-Methoxy-4-methylphenol	20.7	67, 123, 138	Standard	0.99	275.0
2-Methoxy-4-ethylphenol	23.5	137, 152	2-Methoxy-4-methylphenol		
2-Methoxy-4-ethenylphenol	25.4	51, 77, 107, 135, 150	Standard	0.97	251.5
Anhydrosugar derivatives					
(1 <i>S</i> ,5 <i>R</i>)-6,8- Dioxabicyclo[3.2.1]oct-2-en-4- one (layoglucosenone)	19.8	39, 68, 98	Levoglucosan		
1,4:3,6-Dianhydro-α-D-	24.0	69, 86, 98, 144	Levoglucosan		
2,3-Anhydro-D-mannose	24.5	69, 71, 85, 97, 144	Levoglucosan		
1,6-Anhydro-β-D-glucopyranose (levoglucosan)	34.5	60, 73, 126, 145	Standard	0.99	67.0
Naphthalene derivatives			·		
Naphthalene	20.5	51, 102, 128	Standard	0.99	178.8
1-Methylnaphthalene	24.3	71, 115, 142	Naphthalene		
Catechol derivatives	1		I	1	
2,3-Dihydroxybenzaldehyde	20.5	51, 64, 92, 120, 138	Standard	0.99	119.0
1,2-Dihydroxybenzene (catechol)	21.7	64, 81, 110	Standard	0.98	57.3

2',5'-Dihydroxyacetophenone	23.4	69, 109, 137,	2,3-Dihydroxybenzaldehyde		
(1-(2,5-		152			
dihydroxyphenyl)ethanone)					
1,2-Dihydroxy-3-methylbenzene	23.7	51, 78, 106,	Standard	0.97	155.0
		124			
1,2-Dihydroxy-3-	24.4	97, 125, 140	Standard	0.97	159.0
methoxybenzene					
Syringyl derivatives					
2,6-Dimethoxyphenol (syringol)	27.6	96, 139, 154	Standard	0.99	76.3
I. 11					

In all cases, the intercept was 0.0.

^a RT refers to retention time (min).

^b Quantification is done by pure compounds.

^c r² refers to coefficient values.