

This is a self-archived version of an original article. This version may differ from the original in pagination and typographic details.

Author(s): Shen, Hui; Wang, Lingzheng; López-Estrada, Omar; Hu, Chengyi; Wu, Qingyuan; Cao, Dongxu; Malola, Sami; Teo, Boon K.; Häkkinen, Hannu; Zheng, Nanfeng

Title: Copper-hydride nanoclusters with enhanced stability by N-heterocyclic carbenes

Year: 2021

Version: Published version

Copyright: © The Author(s) 2021

Rights: _{CC BY 4.0}

Rights url: https://creativecommons.org/licenses/by/4.0/

Please cite the original version:

Shen, H., Wang, L., López-Estrada, O., Hu, C., Wu, Q., Cao, D., Malola, S., Teo, B. K., Häkkinen, H., & Zheng, N. (2021). Copper-hydride nanoclusters with enhanced stability by N-heterocyclic carbenes. Nano Research, 14(9), 3303-3308. https://doi.org/10.1007/s12274-021-3389-9



Copper-hydride nanoclusters with enhanced stability by Nheterocyclic carbenes

Hui Shen¹, Lingzheng Wang¹, Omar López-Estrada², Chengyi Hu¹, Qingyuan Wu¹, Dongxu Cao¹, Sami Malola², Boon K. Teo¹, Hannu Häkkinen² (🖂), and Nanfeng Zheng¹ (🖂)

¹ State Key Laboratory for Physical Chemistry of Solid Surfaces, Collaborative Innovation Center of Chemistry for Energy Materials, National & Local Joint Engineering Research Center of Preparation Technology of Nanomaterials, College of Chemistry and Chemical Engineering, Xiamen University, Xiamen 361005, China

² Departments of Physics and Chemistry, Nanoscience Center, University of Jyväskylä, FI-40014 Jyväskylä, Finland

© The Author(s) 2021

Received: 25 December 2020/ Revised: 5 February 2021 / Accepted: 8 February 2021

ABSTRACT

Copper-hydrides have been intensively studied for a long time due to their utilization in a variety of technologically important chemical transformations. Nevertheless, poor stability of the species severely hinders its isolation, storage and operation, which is worse for nano-sized ones. We report here an unprecedented strategy to access to ultrastable copper-hydride nanoclusters (NCs), namely, using bidentate N-heterocyclic carbenes as stabilizing ligands in addition to thiolates. In this work, a simple synthetic protocol was developed to synthesize the first large copper-hydride nanoclusters (NCs) stabilized by N-heterocyclic carbenes (NHCs). The NC, with the formula of $Cu_{31}(RS)_{25}(NHC)_3H_6$ (NHC = 1,4-bis(1-benzyl-1H-benzimidazol-1-ium-3-yl) butane, RS = 4-fluorothiophenol), was fully characterized by high resolution Fourier transform ion cyclotron resonance mass spectrum, nuclear magnetic resonance, ultra-violet visible spectroscopy, density functional theory (DFT) calculations and single-crystal X-ray crystallography. Structurally, the title cluster exhibits unprecedented Cu₄ tetrahedron-based vertex-sharing (TBVS) superstructure (fusion of six Cu₄ tetrahedra). Moreover, the ultrahigh thermal stability renders the cluster a model system to highlight the power of NHCs (even other carbenes) in controlling geometrical, electronic and surface structure of polyhydrido copper clusters.

KEYWORDS

metal clusters, copper-hydride, N-heterocylic carbene, stability, superatom

1 Introduction

Unraveling molecular structures and distinct reactivity of coinage metal hydrides has been a hot topic for a long time [1-6]. One benchmark example is the commercially available [Cu₆H₆(PPh₃)₆] (also called Stryker's reagent), which showed a distorted octahedral Cu6 core and could catalyze several chemical reactions including chemoselective hydrogenation of unsaturated ketones, reduction of alkenes and alkynes, and hydrogenation of CO₂ [7-10]. In more recent studies, the structural determination and property investigation of a handful of copper-hydride nanoclusters (NCs), including alkynylprotected Cu₅₃H₁₈ [11], dithiocarbamate-protected Cu₇H [12] and Cu₂₈H₁₅ [13], dithiophosphate-protected Cu₃₂H₂₀ [14] and Cu₂₀H₁₁ [15], thiolate-protected Cu₂₅H₁₀ [6], Cu₃₂H₈ [16] and Cu₈₁H₃₂ [17], and phosphine-protected Cu₁₈H₁₆ [18] and Cu₂₅H₂₂ [19], have mapped out rich hydride coordination modes, diverse structural constructs and atom-precise catalytic sites. Nevertheless, there remains some key issues in this research area: intrinsic instability, sensitivity towards air, limited surface modifiers, and rareness of superstructures, etc. [20].

Interest for coordination chemistry of N-heterocyclic carbenes (NHCs) with coinage metal atoms has been increasing in materials research including complexes, nanoparticles and surfaces [21–24]. In recent reports, this class of ligands were successfully introduced in clusters [22]. Several works on gold NCs, such as Au₃ [25, 26], Au₁₁ [27], Au₁₃ [28, 29], Au₂₅ [30], and Au₄₄ [31], demonstrated that NHCs could endow them with exciting stability, luminescence and reactivity. NHC-stabilized Ag and Cu clusters have also been prepared, in which no hydride was observed [32-37]. In our continuing interest in NHCstabilized nanomaterials, we wish to investigate: (1) Whether NHCs could be employed to stabilize large copper-hydride clusters, thus filling the gap of copper-hydride complexes with carbene ligands and copper nanoparticles; (2) whether Cu NCs stabilized by NHC would exhibit distinct structure, in comparison to those protected by other ligands (phosphines, thiols and alkynyls); (3) whether NHC-stabilized copper-hydride NCs would display unique properties, such as ultrahigh stability, thus could accelerate the understanding and functionalization of Cu nanomaterials at the molecular level.

Herein, we report the first example of large copper-hydride NCs stabilized by NHC ligands: $Cu_{31}(RS)_{25}(NHC)_3H_6$ (hereafter abbreviated as $Cu_{31}H_6$), where NHC is 1,4-bis(1-benzyl-1H-benzimidazol-1-ium-3-yl) butane and RS is 4-fluorothiophenol. The title NC was fully characterized by optical measurement, high-resolution Fourier transform ion cyclotron resonance mass spectroscopy (FTICR-MS), nuclear magnetic resonance (¹H, ²H, and ¹³C NMR) and density functional theory (DFT) calculations. Structurally, "Cu₄ tetrahedron-based vertex-sharing"

Address correspondence to Nanfeng Zheng, nfzheng@xmu.edu.cn; Hannu Häkkinen, hannu.j.hakkinen@jyu.fi



2

(TBVS) superstructure was observed for the first time in Cu NCs. More remarkably, the cluster displayed ultrahigh thermal and air stability.

2 Results and discussion

2.1 Synthesis and characterizations of clusters Cu₃₁H₆

and Cu₃₁D₆

The synthesis of title cluster began with the preparation of bi-dentate NHC ligands. The benzimidazoles were reacted with benzyl chloride, followed by alkylation with a 1,4-dibromobutane to afford the bis-benzimidazolium salts **1b** (Scheme 1, Figs. S1–S4 in the Electronic Supplementary Material (ESM)) [18]. The desired copper complex **1c** was produced by the reaction of equivalent CuCl with **1b** under basic condition (Figs. S5 and S6 in the ESM) [38]. The cluster was prepared in one-pot (see Experimental Section in the ESM for more details). In brief, complex **1c** was reduced by excess NaBH₄ in the presence of stoichiometric thiol to afford a clear orange solution (Figs. S7 and S8 in the ESM). After aging, purification, and further crystallization, bright orange crystals were obtained in the yield of 29.6% (based on Cu).

The sample was first characterized by FTICR-MS in positive mode. $Cu_{31}H_6$ features a signal at m/z 6,439.61 in its FTICR-MS spectra (Fig. 1(a)), which corresponds to the $[Cu_{31}(NHC)_3(RS)_{24}H_6]^+$ ion (calcd m/z 6,439.63). It should be noted that a mass peak corresponding to [Cu₃₁(RS)₂₄(NHC)₃H₆(CH₃CN)]⁺ was also observed (Fig. S9 in the ESM). To further corroborate this composition, we prepared the deuteride analogue, namely, Cu₃₁(RS)₂₅(NHC)₃D₆ (hereafter abbreviated as Cu₃₁D₆), by using NaBD₄ instead of NaBH₄ as the reductant for the synthesis of the clusters. As shown in Fig. 1(a), there was an increase of exactly 6 Da for the $[Cu_{31}(RS)_{24}(NHC)_{3}H_{6}]^{+}$ peak as expected. The experimental UV/Vis spectrum of Cu₃₁H₆ in CH₂Cl₂ is shown in Fig. 1(b). We also recorded the ¹H and ¹³C NMR spectra of Cu₃₁H₆ and Cu₃₁D₆ in CD₂Cl₂ as well as ²H NMR spectrum of Cu₃₁D₆ in CH₂Cl₂ (Figs. S10-S19 in the ESM). The 6 deuterides display two distinct peaks at 2.68 and 3.94 ppm with intensity ratios of 1:1 (Fig. 1(c)), corresponding to the signals at 2.51 and 3.80 ppm in the ¹H NMR spectrum of Cu₃₁H₆ (Fig. S10 in the ESM) in CD₂Cl₂. The appearance of two distinct peaks with intensity ratios of 1:1 strongly suggests the presence of 6 D atoms in the cluster, in two different environments.

2.2 Molecular structure of Cu₃₁H₆ and its hydride positions

The structure of the title cluster Cu₃₁H₆ was determined by



Scheme 1 Preparation of NHC ligand 1b, Cu complex 1c and Cu₃₁H₆.



Figure 1 FTICR-MS, UV/Vis and ²H NMR spectra for Cu₃₁(H/D)₆ clusters. (a) FTICR-MS spectra for Cu₃₁H₆ and Cu₃₁D₆ clusters in the positive mode in CH₂Cl₂. Inset: simulated (red curve) and experimental (black curve) isotope distribution patterns. Note: the peak marked with ϕ corresponds to [Cu₃₁(RS)₂₄(NHC)₃H₆(CH₃CN)]⁺. (b) UV/Vis spectrum of pure [Cu₃₁(RS)₂₅(NHC)₃H₆] crystals dissolved in CH₂Cl₂. (c) ²H NMR spectrum for pure Cu₃₁D₆ cluster in CH₂Cl₂ (Solvent CD₂Cl₂ peak at 5.32 ppm).

single-crystal X-ray diffraction analysis at 100 K (see Table S1 in the ESM for crystallographic data). It crystalizes in the triclinic space group $P\overline{1}$. This revealed that each unit cell contains two independent clusters (Figs. S20–S22 in the ESM), each of which consists of 31 Cu atoms, 25 thiolates, 3 bidentate NHC and 6 hydrides, giving rise to the expected composition of Cu₃₁(RS)₂₅(NHC)₃H₆. Based on peaks in the difference electron density map of the crystallographic data, the positions of the 6 H (or D) atoms were determined and their coordinates were successfully least-squares refined [6, 39].

The structure of individual Cu₃₁H₆ is shown in Fig. 2. It has



Figure 2 Molecular structure of $Cu_{31}(RS)_{25}(NHC)_{3}H_6$. (a) and (d) Total structure in space-filling mode in top and side view; (b) and (e) total structure in ball-and-stick mode in top and side view; (c) and (f) metal framework and hydride position in top and side view. Color legend: sky blue, pink, bright green, lime, and rose, Cu; yellow, S; lavender, F; orange, N; gray, C. H atoms of ligands are omitted for clarity.

an oblate shape (cf. Figs. 2(a) and 2(d)), in sharp contrast to most other Cu hydride clusters. Interestingly, the cluster exhibits a triangular architecture (see Figs. 2(b) and 2(e)). The metal framework conforms to an idealized C₃ symmetry, with one unique Cu atom residing on the C_3 axis (Fig. S23 in the ESM). An anatomy of the inner layer reveals a concaved frequencytwo Cu_{18} triangle (cf. Figs. 2(c) and 2(f)), assembled from six tetrahedral Cu4 units via vertex-sharing. The six tetrahedral units can be divided into two types: Three of them are assembled into a Cu₉ triangular superstructure (Figs. 2(c) and 2(f), rose colored), and remaining three inlay on each edge of the triangle (Figs. 2(c) and 2(f), lime colored). It is worthy noting that for the first time TBVS growth mode was observed in ligated Cu NCs, even the isolated Cu4 tetrahedral kernel has been rarely reported [40]. The discovery of molecular complexity in this cluster indicates certain generality of the supermolecular complexity could also exist in copper clusters [41]. The 12 Cu atoms in the outer layer can also be divided into two categories, according to the coordinating ligands (cf. Figs. 2(b) and 2(e)). They form two sets, three each, of dimers, bridged by thiolate and NHC ligands.

As stated above, two kinds of Cu₄ tetrahedral units are present in Cu₃₁, with average Cu-Cu bond lengths of 2.835 Å (Figs. 2(c) and 2(f), rose colored) and 2.847 Å (Figs. 2(c) and 2(f), lime colored), respectively. These values are comparable to those reported for other related copper hydride clusters, suggesting significant Cu-Cu interactions within the tetrahedral units [42]. In contrast, the interactions between the otherlayer Cu atoms and those in the concave triangle are much weaker, as indicated by their long bond distance (av = 3.203 Å). The average Cu-Cu bond distances bridged by thiolate (pink colored) and NHC ligands (green colored) are measured to be 3.265 and 2.642 Å, respectively. All facial Cu atoms in the triangles were capped by thiolates, with two types of binding modes (μ_3 and μ_2). The Cu atoms bind with NHC ligands tightly, as suggested by the short Cu-C bond length (av = 1.910 Å).

As shown in Figs. 2(c) and 2(f), and Fig. S24 in the ESM, 6 equivalent hydride ligands are clustered into two groups. Each of these hydride ligands exhibit asymmetric μ_4 -coordination in Cu₄ tetrahedra. In the central three tetrahedra, the hydrides are centered in the tetrahedral holes, with short Cu–H bond lengths (average 1.757 Å). The remaining three hydrides were encapsulated in other three tetrahedra with an average Cu–H bond length of 1.755 Å. Overall, this 1:1 arrangement of hydrides is fully consistent with the NMR spectral data.

2.3 DFT calculations for the electronic structure, hydride NMR shifts and optical spectra

We used DFT calculations to explain the electronic and optical properties and confirm the stability of the measured structure of Cu₃₁H₆. The analysis for the electronic ground state and optical spectra were done with GPAW software using a real-space grid (details given in the Experimental Section in the ESM). Relaxation of the structures did not affect the overall symmetry of the cluster. The metal core expanded slightly, which is typical for the used DFT approximation (the Perdew-Burke-Ernzerhof (PBE) exchange-correlation functional). Based on the superatom electron count [43], the cluster should not possess any clear superatomic nature, if assuming hydrides (H⁻) in the core. This was confirmed by the electronic structure analysis shown in Fig. 3(a) that shows no occupied states localized into the metal core close to Fermi energy. The highest occupied molecular orbital (HOMO)-lowest unoccupied molecular orbital (LUMO) energy gap of the cluster is 0.95 eV.



Figure 3 (a) Analysis of the projected density of states in terms of spherical symmetries in the metal core of $Cu_{31}H_6$. The HOMO–LUMO energy gap is centered around zero. (b) Visualization of a few frontier orbitals (each from two directions).

The two highest occupied orbitals are localized mainly in the ligand layer as shown in Fig. 3(b). The LUMO state is the only one having weight in the metal core.

Calculated Bader charges of atoms are shown in Table 1 for the ligands, Cu-atoms and hydrides. The charges confirm the nature of hydrides inside the core as a negatively charged species (-0.288 |e|). Furthermore, the thiolates are clearly with-drawing electrons (-0.418 |e|) whereas NHC-ligands are positively charged (+0.347 |e|). Remarkably, the reaction energy to remove the hydrides from the core is +2.78 eV endothermic. This highlights the importance of the hydrides in stabilizing the structure energetically. The reaction energies were determined with respect to H₂ molecular phase and relaxed cluster structures with and without hydrides based on the experimental starting structure.

We were also able to assign the measured hydride ¹H NMR shifts (2.51 and 3.80 ppm, Fig. S9 in the ESM) to the symmetry environments in the atomic structure (Figs. 2(c) and 2(f)). We calculated the shifts at two levels of theory using the program deMon2k (details in the ESM). The results show consistently (Table 2 below) that the "A-type" hydrides inside the purple

Table 1 Atomic charges of Cu₃₁(SR)₂₅(NHC)₃H₆ cluster

	-		
Atom group	# atoms/ligands N	Total charge Q (e)	Charge per atom/ligand $Q/N(e)$
Cu	31	11 135	0.359
Cu	51	11.155	0.557
NHC	3	1.041	0.347
SR	25	-10.445	-0.418
Н	6	-1.727	-0.288

Table 2 DFT ¹H chemical shift δ mean value $\overline{\delta}$ and standard deviation σ in ppm of Cu₃₁(SR)₂₅(NHC)₃H₆

Method		δ		$\overline{\delta}$	σ
	A1	A2	A3		
	1.81	2.84	2.20	2.28	0.52
PDE/SDD/DZVP	B1	B2	B3		
	4.16	4.87	4.51	4.51	0.36
	A1	A2	A3		
	3.02	3.82	3.60	3.48	0.41
PBE/DZVP-ALL	B1	B2	B3		
	4.88	5.32	5.03	5.08	0.22

 Cu_4 tetrahedra in Figs. 2(c) and 2(f) have a smaller shift (are better magnetically shielded) as compared to "B-type" hydrides inside the green Cu_4 tetrahedra in Figs. 2(c) and 2(f).

To analyse further the experimental observations, the optical absorption spectra were calculated for the relaxed hydride and non-hydride clusters using linear response time-dependent density functional theory (lr-TDDFT) as implemented in GPAW. The calculated optical absorption spectrum of the hydride cluster is in good agreement with the experimental spectrum as shown in Fig. 4. The first increase in the intensity of the spectrum of Cu₃₁H₆ is seen around 700 nm in the calculated spectrum which can be correlated with the similar turning point at 600 nm in the experimental spectrum (Fig. 1(b)). The second change in the slope of the calculated spectrum is seen around 460 nm, below which there is a rapid increase in the intensity. A similar behavior is seen in the experimental spectrum below 400 nm. The couple of faint features observed in the calculated spectrum go well along with these intensity changes. Figure 4 also shows that the model cluster without hydrides yields a computed spectrum that extends well beyond



Figure 4 The calculated optical spectra of the hydride and non-hydride Cu₃₁ clusters.

1,100 nm, which is not in agreement with the observed data. This again confirms the existence of the hydrides in the experiment.

Finally, molecular dynamics simulations were done for the cluster with and without hydrides to see whether the structure remain stable also at increasing temperatures, see Movies ESM1 and ESM2. Interestingly, neither of the structures show any major deformations at the room temperature during the 4.3–4.5 ps runs including heating. One plausible explanation is that the metal core is oblate which confirms with the optimal shape of a stable 6e superatom (hypothetical non-hydride Cu_{31} cluster). Based on calculations, it can be concluded that the observed structural symmetry of $Cu_{31}H_6$ is unique for dynamical stability both with and without the hydride atoms in the core. However, hydrides are needed to make the cluster energetically more stable and to reproduce the experimentally observed optical properties.

2.4 Stability of Cu₃₁ in solution

The instability of copper-hydride NCs has limited their practical applications, which probably results from active nature of hydride species [5]. To our surprise, Cu₃₁ is unusually stable. As shown in Fig. S26 in the ESM, there is no obvious color change upon heating solution of Cu₃₁H₆ at 50 °C in air for 6 h. ²H NMR track of Cu₃₁D₆ showed that the two peaks of Cu₃₁D₆ exhibits no decomposition and no new peak formed in the whole process, indicating that the hydrides in Cu₃₁ were strongly stabilized (Fig. 5(a)). The high robustness of Cu₃₁D₆ in CHCl₃ up to at least 12 h was suggested by ²H NMR measurements (Fig. S27 in the ESM). Moreover, UV/Vis profile of Cu₃₁H₆ was practically unchanged during the heating process (Fig. 5(b)), and the relative intensity of the peak at 377 nm as a function of heating time (Fig. 5(e), black curve) showed almost no degradation in the thermal measurement, again proving the ultra-high stability of Cu₃₁. As comparison, allthiolate-stabilized [Cu₆₁(S^tBu)₂₆S₆Cl₆H₁₄]⁺ (Cu₆₁) [44] deteriorates progressively in the heating period (Fig. 5(c)), and the relative absorbance intensity decreases gradually (Fig. 5(e), red curve). Furthermore, all-phosphine-protected Cu₂₅H₂₂((p-FPh)₃P)₁₂ (Cu₂₅) [45] exhibited much worse stability (Fig. 5(c) and pink



Figure 5 Stability comparison of Cu_{31} with other Cu clusters: (a) real-time tracking ²H NMR for $Cu_{31}D_6$ clusters at 50 °C in air in CHCl₃ (solvent CDCl₃ peak at 7.26 ppm); (b) and (c) real-time tracking UV/Vis spectra for Cu_{31} , Cu_{61} and Cu_{25} clusters dissolved in 1,2-dichloroethane upon heating at 50 °C in air; (d) relative absorbance intensity of peaks at 377 nm.

curve in Fig. 5(d)). We attribute the ultra-high stability of Cu_{31} to be the same reason as in NHC-protected gold NCs, namely, unusually strong metal–carbene bonds [28].

3 Conclusions

In conclusion, a one-pot synthetic strategy was developed to access to the first N-heterocyclic carbene-stabilized copperhydride nanoclusters. Metal framework of the cluster displays unprecedented "Cu4 tetrahedron-based vertex-sharing" growth mode, suggesting the generality of molecular superstructure in ligated copper NCs. DFT calculations confirm the role of hydrides to stabilize the structure energetically and to produce the measured optical absorption. We were also able to assign the measured hydride NMR shifts to symmetry environments in the observed structure. Moreover, we confirmed that the dynamical stability of the cluster is unique but is not strongly dependent on existence of hydrides. We hope that the ultrahigh thermal and oxidation stability reported in this article will trigger more interests in the synthesis, structure, and properties of high-nuclearity copper hydride nanoclusters involving carbenes. More work, including extending the synthetic method to more underlying ones, and systematic studying their reactivity is under investigation.

Acknowledgements

We thank the National Key R&D Program of China (No. 2017YFA0207302), the National Natural Science Foundation of China (Nos. 21890752, 21731005, 21420102001, and 21721001) and the 111 Project (No. B08027) for financial support. The computational work in the University of Jyväskylä was supported by the Academy of Finland through HH's Academy Professorship and grants 292352, 319208. H. H. acknowledges support from China's National Innovation and Intelligence Introduction Base visitor program. The computations were made at the CSC supercomputing center in Finland. We thank L. Feng from High-Field Nuclear Magnetic Resonance Research Center (Xiamen University) for the help in the NMR studies.

Funding note: Open access funding provided by University of Jyväskylä (JYU).

Electronic Supplementary Material: Supplementary material (detailed synthesis and characterization including NMR spectra, DPVs and videos for molecular dynamics simulations of the clusters with and without hydrides) is available in the online version of this article at https://doi.org/10.1007/s12274-021-3389-9.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made.

The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit http://creativecommons.org/licenses/by/4.0/.

References

- Shi, S. L.; Wong, Z. L.; Buchwald, S. L. Copper-catalysed enantioselective stereodivergent synthesis of amino alcohols. *Nature* 2016, *532*, 353–356.
- [2] Yang, Y.; Shi, S. L.; Niu, D. W.; Liu, P.; Buchwald, S. L. Catalytic asymmetric hydroamination of unactivated internal olefins to aliphatic amines. *Science* 2015, 349, 62–66.
- [3] Zhu, S. L.; Niljianskul, N.; Buchwald, S. L. A direct approach to amines with remote stereocentres by enantioselective CuH-catalysed reductive relay hydroamination. *Nat. Chem.* 2016, *8*, 144–150.
- [4] Zall, C. M.; Linehan, J. C.; Appel, A. M. Triphosphine-ligated copper hydrides for CO₂ hydrogenation: Structure, reactivity, and thermodynamic studies. *J. Am. Chem. Soc.* **2016**, *138*, 9968–9977.
- [5] Jordan, A. J.; Lalic, G.; Sadighi, J. P. Coinage metal hydrides: Synthesis, characterization, and reactivity. *Chem. Rev.* 2016, *116*, 8318–8372.
- [6] Sun, C. F.; Mammen, N.; Kaappa, S.; Yuan, P.; Deng, G. C.; Zhao, C. W.; Yan, J. Z.; Malola, S.; Honkala, K.; Häkkinen, H. et al. Atomically precise, thiolated copper-hydride nanoclusters as singlesite hydrogenation catalysts for ketones in mild conditions. ACS Nano 2019, 13, 5975–5986.
- [7] Bezman, S. A.; Churchill, M. R.; Osborn, J. A.; Wormald, J. Preparation and crystallographic characterization of a hexameric triphenylphosphinecopper hydride cluster. J. Am. Chem. Soc. 1971, 93, 2063–2065.
- [8] Lipshutz, B. H.; Frieman, B. A. CuH in a bottle: A convenient reagent for asymmetric hydrosilylations. *Angew. Chem., Int. Ed.* 2005, 44, 6345–6348.
- [9] Mahoney, W. S.; Brestensky, D. M.; Stryker, J. M. Selective hydridemediated conjugate reduction of α,β-unsaturated carbonyl compounds using [(Ph₃P)CuH]₆. J. Am. Chem. Soc. **1988**, 110, 291–293.
- [10] Lemmen, T. H.; Foiling, K.; Huffman, J. C.; Caulton, K. G. Copper polyhydrides. J. Am. Chem. Soc. 1985, 107, 7774–7775.
- [11] Yuan, P.; Chen, R. H.; Zhang, X. M.; Chen, F. J.; Yan, J. Z.; Sun, C. F.; Ou, D. H.; Peng, J.; Lin, S. C.; Tang, Z. C. et al. Ether-soluble Cu₅₃ nanoclusters as an effective precursor of high-quality CuI films for optoelectronic applications. *Angew. Chem., Int. Ed.* **2019**, *58*, 835–839.
- [12] Liao, P. K.; Fang, C. S.; Edwards, A. J.; Kahlal, S.; Saillard, J. Y.; Liu, C. W. Hydrido copper clusters supported by dithiocarbamates: Oxidative hydride removal and neutron diffraction analysis of [Cu₇(H){S₂C(aza-15-crown-5)}₆]. *Inorg. Chem.* **2012**, *51*, 6577–6591.
- [13] Edwards, A. J.; Dhayal, R. S.; Liao, P. K.; Liao, J. H.; Chiang, M. H.; Piltz, R. O.; Kahlal, S.; Saillard, J. Y.; Liu, C. W. Chinese puzzle molecule: A 15 hydride, 28 copper atom nanoball. *Angew. Chem., Int. Ed.* 2014, *53*, 7214–7218.
- [14] Dhayal, R. S.; Liao, J. H.; Kahlal, S.; Wang, X. P.; Liu, Y. C.; Chiang, M. H.; van Zyl, W. E.; Saillard, J. Y.; Liu, C. W. [Cu₃₂(H)₂₀{S₂P(OⁱPr)₂}₁₂]: The largest number of hydrides recorded in a molecular nanocluster by neutron diffraction. *Chem.—Eur. J.* 2015, 21, 8369–8374.
- [15] Dhayal, R. S.; Liao, J. H.; Wang, X. P.; Liu, Y. C.; Chiang, M. H.; Kahlal, S.; Saillard, J. Y.; Liu, C. W. Diselenophosphate-induced conversion of an achiral [Cu₂₀H₁₁{S₂P(OⁱPr)₂}₉] into a chiral [Cu₂₀H₁₁{Se₂P(OⁱPr)₂}₉] polyhydrido nanocluster. *Angew. Chem., Int. Ed.* **2015**, *54*, 13604–13608.
- [16] Lee, S.; Bootharaju, M. S.; Deng, G; Malola, S.; Baek, W.; Häkkinen, H.; Zheng, N. F.; Hyeon, T. [Cu₃₂(PET)₂₄H₈Cl₂](PPh₄)₂: A copper hydride nanocluster with a bisquare antiprismatic core. *J. Am. Chem. Soc.* **2020**, *142*, 13974–13981.
- [17] Huang, R. W.; Yin, J.; Dong, C. W.; Ghosh, A.; Alhilaly, M. J.; Dong, X. L.; Hedhili, M. N.; Abou-Hamad, E.; Alamer, B.; Nematulloev, S. et al. [Cu₈₁(PhS)₄₆(¹BuNH₂)₁₀(H)₃₂]³⁺ reveals the coexistence of large planar cores and hemispherical shells in high-nuclearity copper nanoclusters. *J. Am. Chem. Soc.* **2020**, *142*, 8696–8705.
- [18] Li, J. Y.; Ma, H. Z.; Reid, G. E.; Edwards, A. J.; Hong, Y. N.; White, J. M.; Mulder, R. J.; O'Hair, R. A. J. Synthesis and X-ray crystallographic characterisation of frustum-shaped ligated [Cu₁₈H₁₆(DPPE)₆]²⁺ and [Cu₁₆H₁₄(DPPA)₆]²⁺ nanoclusters and studies on their H₂ evolution reactions. *Chem.—Eur. J.* **2018**, *24*, 2070–2074.

- [19] Nguyen, T. A.; Jones, Z. R.; Goldsmith, B. R.; Buratto, W. R.; Wu, G.; Scott, S. L.; Hayton, T. W. A Cu₂₅ nanocluster with partial Cu(0) character. J. Am. Chem. Soc. 2015, 137, 13319–13324.
- [20] Sun, C. F.; Teo, B. K.; Deng, C. L.; Lin, J. Q.; Luo, G. G; Tung, C. H.; Sun, D. Hydrido-coinage-metal clusters: Rational design, synthetic protocols and structural characteristics. *Coordin. Chem. Rev.* 2021, 427, 213576.
- [21] Hopkinson, M. N.; Richter, C.; Schedler, M.; Glorius, F. An overview of N-heterocyclic carbenes. *Nature* 2014, 510, 485–496.
- [22] Smith, C. A.; Narouz, M. R.; Lummis, P. A.; Singh, I.; Nazemi, A.; Li, C. H.; Crudden, C. M. N-Heterocyclic carbenes in materials chemistry. *Chem. Rev.* 2019, *119*, 4986–5056.
- [23] Zhao, Q.; Meng, G. R.; Nolan, S. P.; Szostak, M. N-Heterocyclic carbene complexes in C–H activation reactions. *Chem. Rev.* 2020, 120, 1981–2048.
- [24] Zhukhovitskiy, A. V.; MacLeod, M. J.; Johnson, J. A. Carbene ligands in surface chemistry: From stabilization of discrete elemental allotropes to modification of nanoscale and bulk substrates. *Chem. Rev.* 2015, *115*, 11503–11532.
- [25] Robilotto, T. J.; Bacsa, J.; Gray, T. G.; Sadighi, J. P. Synthesis of a trigold monocation: An isolobal analogue of [H₃]⁺. Angew. Chem., Int. Ed. 2012, 51, 12077–12080.
- [26] Jin, L. Q.; Weinberger, D. S.; Melaimi, M.; Moore, C. E.; Rheingold, A. L.; Bertrand, G. Trinuclear gold clusters supported by cyclic (alkyl)(amino)carbene ligands: Mimics for gold heterogeneous catalysts. *Angew. Chem., Int. Ed.* **2014**, *53*, 9059–9063.
- [27] Narouz, M. R.; Osten, K. M.; Unsworth, P. J.; Man, R. W. Y.; Salorinne, K.; Takano, S.; Tomihara, R.; Kaappa, S.; Malola, S.; Dinh, C. T. et al. N-Heterocyclic carbene-functionalized magic-number gold nanoclusters. *Nat. Chem.* **2019**, *11*, 419–425.
- [28] Narouz, M. R.; Takano, S.; Lummis, P. A.; Levchenko, T. I.; Nazemi, A.; Kaappa, S.; Malola, S.; Yousefalizadeh, G.; Calhoun, L. A.; Stamplecoskie, K. G. et al. Robust, highly luminescent Au₁₃ superatoms protected by N-heterocyclic carbenes. *J. Am. Chem. Soc.* **2019**, *141*, 14997–15002.
- [29] Shen, H.; Xiang, S. J; Xu, Z.; Liu, C.; Li, X. H.; Sun, C. F.; Lin, S. C.; Teo, B. K.; Zheng, N. F. Superatomic Au₁₃ clusters ligated by different N-heterocyclic carbenes and their ligand-dependent catalysis, photoluminescence, and proton sensitivity. *Nano Res.* 2020, *13*, 1908–1911.
- [30] Shen, H.; Deng, G. C.; Kaappa, S.; Tan, T. D.; Han, Y. Z.; Malola, S.; Lin, S. C.; Teo, B. K.; Hakkinen, H.; Zheng, N. F. Highly robust but surface-active: An N-heterocyclic carbene-stabilized Au₂₅ nanocluster. *Angew. Chem., Int. Ed.* **2019**, *58*, 17731–17735.
- [31] Shen, H.; Xu, Z.; Hazer, M. S. A.; Wu, Q. Y.; Peng, J.; Qin, R. X.; Malola, S.; Teo, B. K.; Häkkinen, H.; Zheng, N. F. Surface coordination of multiple ligands endows N-heterocyclic carbene-stabilized gold nanoclusters with high robustness and surface reactivity. *Angew. Chem., Int. Ed.* 2021, *133*, 3796–3802.

- [32] Khalili Najafabadi, B. Corrigan, J. F. N-Heterocyclic carbene stabilized Ag-P nanoclusters. *Chem. Commun.* 2015, *51*, 665–667.
- [33] Peltier, J. L.; Soleilhavoup, M.; Martin, D.; Jazzar, R.; Bertrand, G. Absolute templating of M(111) cluster surrogates by galvanic exchange. J. Am. Chem. Soc. 2020, 142, 16479–16485.
- [34] Makarem, A.; Berg, R.; Rominger, F.; Straub, B. F. A fluxional copper acetylide cluster in CuAAC catalysis. *Angew. Chem., Int. Ed.* 2015, 54, 7431–7435.
- [35] Humenny, W. J.; Mitzinger, S.; Khadka, C. B.; Najafabadi, B. K.; Vieira, I.; Corrigan, J. F. N-Heterocyclic carbene stabilized copper- and silver-phenylchalcogenolate ring complexes. *Dalton Trans.* 2012, *41*, 4413–4422.
- [36] Drescher, W.; Borner, C.; Kleeberg, C. Stability and decomposition of copper(I) boryl complexes: [(IDipp)Cu–Bneop], [(IDipp*)Cu–Bneop] and copper clusters. *New J. Chem.*, in press, DOI: 10.1039/d0nj03166f.
- [37] Chen, C.; Qiu, H. Y.; Chen, W. Z. Trinuclear copper(I) complex of 1,3-bis(2-pyridinylmethyl)imidazolylidene as a carbene-transfer reagent for the preparation of catalytically active nickel(II) and palladium(II) complexes. J. Organomet. Chem. 2012, 696, 4166–4172.
- [38] Korotkikh, N. I.; Saberov, V. S.; Kiselev, A. V.; Glinyanaya, N. V.; Marichev, K. A.; Pekhtereva, T. M.; Dudarenko, G. V.; Bumagin, N. A.; Shvaika, O. P. Heterocyclic carbene complexes of nickel, palladium, and copper(I) as effective catalysts for the reduction of ketones. *Chem. Heterocycl. Comp.* **2012**, *47*, 1551–1560.
- [39] Yuan, X. T.; Sun, C. F.; Li, X. H.; Malola, S.; Teo, B. K.; Häkkinen, H.; Zheng, L. S.; Zheng, N. F. Combinatorial identification of hydrides in a ligated Ag₄₀ nanocluster with noncompact metal core. *J. Am. Chem. Soc.* 2019, *141*, 11905–11911.
- [40] Han, B. L.; Liu, Z.; Feng, L.; Wang, Z.; Gupta, R. K.; Aikens, C. M.; Tung, C. H.; Sun, D. Polymorphism in atomically precise Cu₂₃ nanocluster incorporating tetrahedral [Cu₄]⁰ kernel. J. Am. Chem. Soc. 2020, 142, 5834–5841.
- [41] Zeng, C. J.; Chen, Y. X.; Liu, C.; Nobusada, K.; Rosi, N. L.; Jin, R. C. Gold tetrahedra coil up: Kekulé-like and double helical superstructures. *Sci. Adv.* 2015, *1*, e1500425.
- [42] Qu, M.; Zhang, F. Q.; Wang, D. H.; Li, H.; Hou, J. J.; Zhang, X. M. Observation of non-FCC copper in alkynyl-protected Cu₅₃ nanoclusters. *Angew. Chem., Int. Ed.* **2020**, *59*, 6507–6512.
- [43] Walter, M.; Akola, J.; Lopez-Acevedo, O.; Jadzinsky, P. D.; Calero, G.; Ackerson, C. J.; Whetten, R. L.; Grönbeck, H.; Häkkinen, H. A unified view of ligand-protected gold clusters as superatom complexes. *Proc. Natl. Acad. Sci. USA* 2008, *105*, 9157–9162.
- [44] Ghosh, A.; Huang, R. W.; Alamer, B.; Abou-Hamad, E.; Hedhili, M. N.; Mohammed, O. F.; Bakr, O. M. [Cu₆₁(S'Bu)₂₆S₆Cl₆H₁₄]⁺: A core-shell superatom nanocluster with a Quasi-J₃₆ Cu₁₉ core and an "18-Crown-6" metal-sulfide-like stabilizing belt. ACS Materials Lett. **2019**, *1*, 297–302.
- [45] Chen, A. L.; Kang, X.; Jin, S.; Du, W. J.; Wang, S. X.; Zhu, M. Z. Gram-scale preparation of stable hydride M@Cu₂₄ (M = Au/Cu) nanoclusters. *J. Phys. Chem. Lett.* **2019**, *10*, 6124–6128.